

## **1** HIT THE BASE:

Laying flat base surface to be cleaned, there can be uneven, and then use the toothed trowel smooth paste adhesives in scrapings on the wave pattern and control the temperature between 5 degrees Celsius to 39 degrees Celsius.

## **2** PAVING:

Paving mosaic, note associated with the United same width between the left seam, paving process is the most important aspects to have the patience to paving, stickers bad will affect the overall results.

## **3** COMPACTED SURFACE:

Gently press the mosaic mosaic paved surface, leveling the surface and allowed to eat the pulp evenly, keeping the same mosaic surface height.

## **4** CAULK:

About 1 hour, paste completely after condensation with a sponge trowel grout knife to fill the gap, the gap is not filled with mosaics easily accumulate dust, clean the difficulties brought about in the future.

## **5** CLEAN:

Before the agent of caulking dry, about 1 hour after cleaning the surface of the Mosaic, prepare a bucket of clean water, use a sponge or towel erase a soft material such as Mosaic surface excess gap filling agent, once again, the best surface until clean with a towel.

## **6** DAILY CLEANING:

Available water wipe the surface of the Mosaic in everyday life as a daily regular cleaning, if in certain cases encountered stubborn stains stone cleaner, but please note that after the clean must wash immediately with plenty of water.

PLEASE USE NEUTRAL MOSAIC SPECIAL ADHESIVES

### GRAPHIC MOSAIC CONSTRUCTION



① HIT THE BASE:



② PAVING:



③ COMPACTED SURFACE:



④ CAULK:



⑤ CLEAN: