



PORCH & PATIO FLOOR PAINT LOW-LUSTRE ENAMEL
NO. 6050 ULTRA PURE WHITE®

PRODUCT INFORMATION

BEHR PREMIUM® Porch & Patio Floor Paint is available in two sheens, Low-Lustre and Gloss Enamels. This 100% acrylic latex product, has a mildew resistant finish, resists scuffing, fading, cracking and peeling while providing a durable, long-lasting finish that is ideal for both interior and exterior applications.

RECOMMENDED USES:

This product is ideal for porches, floors, decks, basements, patios, siding, trim, furniture and trellises. Not for use on garage floors or areas subject to automotive traffic. Use on previously painted or primed interior or exterior surfaces such as:

- Wood
- Concrete
- Composite

PRODUCT SPECIFICATIONS:

Tint Bases/Max Tint Load:

- No. 6050 Ultra White Base 126 fl oz / 4 fl oz
- No. 6300 Deep Base 116 fl oz / 14 fl oz

PRE-MIXED COLORS:

No. 6695 Low-Lustre Slate Gray

Gloss: 5 – 15 @ 60°

Sheen: 5 – 15 @ 85°

Resin Type: 100% Acrylic

Weight per Gallon: 10.7 lb

% Solids by Volume: 37% ± 2%

% Solids by Weight: 49% ± 2%

VOC: < 50 g/L

Flash Point: N/A

Viscosity: 90 – 100 KU

Recommended Film Thickness:

- Wet: 8.0 mils / Dry: 3.0 mils @ 200 sq ft/gal
- Wet: 4.0 mils / Dry: 1.5 mils @ 400 sq ft/gal

Coverage: 200 – 400 sq ft/gal depending on application method and substrate porosity. Does not include the loss of material from spraying.

APPLICATION:

Brush: Nylon/polyester

Roller: 3/8" – 3/4" nap roller cover, depending on surface texture

Airless Spray:

- Tip:** .015" – .019"
- Filter:** 60 mesh

Thinning: If required, thin with water at a rate of no more than 1/2 pint per gallon.

Dry Time: 77°F & 50% RH

To Touch: 1 hour

To Recoat: 4 – 6 hours

Full Cure: 4 weeks

Longer dry time may be required in cooler temperatures and higher humidity. Allow 72 hours before subjecting to normal use.

SURFACE PREPARATION:

All surfaces must be clean, free of dust, chalk, oil, grease, wax, polish, mold and mildew stains, loose and peeling paint, rust and all other foreign substances.

Drywall: All drywall surfaces should be sufficiently sanded smooth. Remove any remaining drywall dust prior to priming. Allow all drywall compounds to be completely dry prior to coating.

Wood: Remove mill glaze with sandpaper or use a product such as BEHR PREMIUM® All-In-One Wood Cleaner No. 63 (exterior only) to open the pores of the wood and follow all label instructions. For severe stains caused by mold, mildew, algae and fungus, apply a mildew stain removing product. Set nails and fill holes, scratches, and gouges with the appropriate wood filler and let dry completely. Remove all dust with a wiping cloth. Fill all gaps with a 100% acrylic, siliconized, paintable caulking and allow to dry completely. Patched and filled surfaces should be sanded smooth and dusted clean prior to coating. **WARNING!** Sanding or scraping pressure treated lumber may be hazardous; wear appropriate protection.

Masonry: Allow to cure for 30 days. The pH must be 10 or lower prior to coating. Remove bond breakers and all form release and curing agents. Smooth masonry may require an adequate profile for adhesion. Remove all loose aggregate and debris. If painting cannot wait 30 days or pH level is above 10, allow the surface to cure 7 days and prime the surface with an alkali-resistant primer

COMPLIES WITH THE BELOW AS OF 6/1/2020			
SCAQMD	YES	LADCO	YES
CARB SCM 2007	YES	AIM	YES
OTC PHASE II	YES	GREENGUARD®#	YES
OTC	YES	LEED® v.4‡	YES

This coating conforms to USDA regulatory requirements for incidental food-contact materials intended for use on surfaces not in direct contact with food, such as walls, floors and ceilings.

*GREENGUARD is a registered trademark of UL Company

‡Please visit www.usgbc.org/LEED for additional details.

Plaster: New plaster should be thoroughly dried out and cured for a minimum of 30 days before painting. When cured, clean using a mixed solution of one part vinegar and one part water to remove efflorescence and neutralize. Prime the area with an alkali-resistant primer.

Steel: Minimum surface preparation is Hand Tool Cleaning in accordance with SSPC-SP2. Remove all oil and grease from the surface with a solvent in accordance with SSPC-SP1. For optimal performance, use Commercial Blast Cleaning in accordance with SSPC-SP6. Prime the area with a rustinhibitive primer the same day as cleaned.

Galvanized Steel: Solvent clean new galvanized metal in accordance with SSPC-SP1 to remove oil and grease from the surface. Pre-treat with a phosphoric acid solution or a commercially-available etching solution. Galvanized metal that has been passivated with chromates or silicates may require brush blasting in accordance with SSPC-SP16 to remove these treatments. Rusty galvanizing requires a minimum of Hand Tool Cleaning in accordance with SSPC-SP2. Prime the area the same day as cleaned..

Shop-Primed Steel: As there is potential for many forms of contamination during storage and transport, a thorough cleaning is always recommended for shop-primed surfaces. Paint exposed areas, i.e., where shop primer is abraded, with the same material as used for shop priming to comply with SSPC-PA 1 for touching up shop-primed surfaces. Note: Assess the integrity of the shop primer prior to application of subsequent coatings. Review all coatings intended for the project and confirm the compatibility between shop and field-applied coatings..

Aluminum: Remove all oil and grease from the surface with a solvent in accordance with SSPC-SP1. Prime the area the same day as cleaned.





PORCH & PATIO FLOOR PAINT LOW-LUSTRE ENAMEL

NO. 6050 ULTRA PURE WHITE®

Stain-Blocking: After priming, test for stain bleed-through by applying the topcoat to a small section. If the stain bleeds through the topcoat, apply a second coat of primer and test again before topcoating the entire area. If bleeding continues, primer may need a longer dry time before applying topcoat.

Previously Painted Surfaces: Remove all loose and peeling paint and all other foreign substances. Clean any dirt and grease by scrubbing the surface with a detergent and water solution, followed by a thorough rinsing with clean water. Set nails and fill holes, scratches, and gouges with the appropriate wood filler and let dry completely. Remove all dust with a tack or wiping cloth. Fill all gaps with a 100% acrylic, siliconized, paintable caulking, and allow to completely dry prior to coating.

Glossy Surfaces: For maximum adhesion, sand the surface thoroughly to provide a rough surface before coating.

WARNING! If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Center at 1-800-424-LEAD or log on to www.epa.gov/lead

RECOMMENDED PRIMER/SYSTEMS:

Wood:

- 1 coat BEHR® Kitchen, Bath & Trim Interior Stain-Blocking Primer & Sealer No. 75 (vertical & interior only) or BEHR® Multi-Surface Interior/Exterior Stain-Blocking Primer & Sealer No. 436
2 coats BEHR PREMIUM Porch & Patio Floor Paint

Stain-Blocking:

- 1 coat BEHR® Kitchen, Bath & Trim Interior Stain-Blocking Primer & Sealer No. 75 (vertical & interior only) or BEHR® Multi-Surface Interior/Exterior Stain-Blocking Primer & Sealer No. 436
2 coats BEHR PREMIUM Porch & Patio Floor Paint

Masonry:

- 1 coat BEHR Kitchen, Bath & Trim Interior Stain-Blocking Primer & Sealer No. 75 (vertical & interior only), BEHR PREMIUM Concrete & Masonry Bonding Primer No. 880 or BEHR Multi-Surface Interior/Exterior Stain-Blocking Primer & Sealer No. 436
2 coats BEHR PREMIUM Porch & Patio Floor Paint

Ferrous and Non-Ferrous Metals:

- 1 coat BEHR Interior/Exterior Metal Primer No. 435 (recommended for optimal corrosion resistance or when priming over sound rusty metal surfaces) or BEHR Multi-Surface Interior/Exterior Stain-Blocking Primer & Sealer No. 436
2 coats BEHR PREMIUM Porch & Patio Floor Paint

Vinyl Siding, Architectural Plastics:

- 1 coat BEHR Multi-Surface Interior/Exterior Stain-Blocking Primer & Sealer No. 436
2 coats BEHR PREMIUM Porch & Patio Floor Paint

CLEAN-UP/DISPOSAL:

Clean all tools and equipment with warm, soapy water. Do not dispose of this product down a drain. If spilled, contain material and remove with an inert absorbent. Dispose of contaminated absorbent, container and unused product in accordance with all current federal, state and local regulations. For recycling or disposal of empty containers, unused product and soiled rags, contact your household refuse collection service.

CAUTIONS/LIMITATIONS:

- Protect from freezing.
- Do not use on garage floors and driveways.
- Do not use on roofs.
- For best results, apply when air, material and surface temperatures are between 50°F and 90°F. Do not apply in direct sunlight. Temperatures above 90°F can cause the paint to dry too fast, whereas temperatures below 50°F can inhibit proper film formation. NOTE: If the surface is hot to the touch it should be considered too hot to apply this coating.
- Allow 72 hours before subjecting to normal use.
- After 30 days, cured paint film may be cleaned with a mild, non-abrasive liquid detergent.
- Shelf life under normal conditions is two years unopened.

GENERAL INFORMATION:

CAUTION IRRITANT HARMFUL IF SWALLOWED. MAY CAUSE EYE, NOSE AND THROAT IRRITATION. AVOID CONTACT WITH SKIN AND EYES AND AVOID BREATHING OF VAPORS AND SPRAY MIST. WEAR EYE PROTECTION AND PROTECTIVE CLOTHING. USE ONLY WITH ADEQUATE VENTILATION. To avoid breathing vapors and spray mist, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches or dizziness, increase fresh air. If properly used, a respirator (NIOSH approved for organic vapor with P series particulate pre-filter) may offer additional protection; obtain professional advice before using. A dust mask does not provide protection against vapors. Avoid contact with eyes and skin. Wash thoroughly after handling. Close container after each use.

FIRST AID: If you experience difficulty in breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical assistance immediately. In case of eye contact, flush immediately with plenty of water for at least 20 minutes and get medical attention; for skin, wash thoroughly with soap and water. If swallowed, get medical attention immediately.

CAUTION: KEEP OUT OF REACH OF CHILDREN – DO NOT TAKE INTERNALLY.