BEHR PREMIUM® WITH HEAT-REDUCING TECHNOLOGY

PORCH & PATIO FLOOR PAINT NO. 6210 (LOW-LUSTRE) FROSTED GRAY BASE

BEHR PREMIUM® Porch & Patio Floor Paint with Heat-Reducing Technology helps lower surface temperature up to 15°F*. This l00% acrylic latex product , has a mildew resistant finish, resists scuffing, fading, cracking and peeling while providing a durable, long-lasting finish that is ideal for both interior and exterior applications.

This product is ideal for porches, decks, basement floors, patios, spindles, and railings. Not for industrial use or areas subject to automotive tires. Use on properly prepared, uncoated or previously painted interior/exterior surfaces such as:

- Wood
- Concrete

PRODUCT SPECIFICATIONS

Tint Bases/Max Tint Load:
No. 6210 Frosted Gray Base 124 oz. / 6 oz.

Pre-Mixed Color:
6220 Low-Lustre Cool Slate Gray

Gloss: 5–15 @ 60°
Sheen: 5–15 @ 85°

Resin Type: 100% Acrylic

Weight per Gallon: 10.0 lbs.

% Solids by Volume: 33.2%

% Solids by Weight: 44.5%

VOC: <50 g/L

Flash Point: N/A

Viscosity: 90–100 KU

Recommended Film Thickness:
Wet: 8.0 Dry: 2.7 mils @ 200 sq ft/gal
Wet: 4.0 Dry: 1.3 mils @ 400 sq ft/gal

Coverage: 200-400 sq ft/gal depending on application method and substrate porosity. Does not include the loss of material from spraying.

COMPLIANCE & CERTIFICATIONS

Complies with the below as of 9/1/2025

SCAQMD	YES	OTC	YES
CARB SCM 2020	YES	LADCO	YES
CARB SCM 2007	YES	EPA AIM	YES
OTC Phase II	YES		

This coating conforms to USDA regulatory requirements for incidental food-contact materials intended for use on surfaces not in direct contact with food, such as walls, floors and ceilings.

APPLICATION

Brush: Nylon/polyester

Roller: ⅜"–½" nap

Airless Spray: At packaged consistency

Tip: .015"– .017"

Filter: 60 mesh

Thinning: (If required) No more than ½ pint of water per gallon.

Dry Time: @ 77° & 50% RH
Longer dry time may be required in cooler temperatures and higher humidity.

To Touch: 1 hour
To Recoat: 4–6 hours
Full Cure: 2 weeks. Allow 72 hours before subjecting to normal use. After 30 days, cured paint film may be cleansed with a mild, non-abrasive liquid detergent.

SURFACE PREPARATION

All surfaces must be clean, free of dust, chalk, oil, grease, wax, polish, mold and mildew stains, loose and peeling paint, rust and all other foreign substances.

CAUTION: Vinyl siding is manufactured to withstand certain levels of heat intensity. Be sure when choosing a paint color, to select a color which is similar or lighter than the vinyl siding's original color. A darker color paint will absorb more heat, resulting in a warping of the siding.

Wood: Shakes & Shingles, Composition Panels/ Siding, Fiber Board: New Wood: Remove mill glaze with sandpaper or use a product such as BEHR PREMIUM® All-in-One Wood Cleaner No. 63 to open the pores of the wood and follow all label instructions. Remove mildew stains with a mildew stain removing product. Set nails and fill holes, scratches, and gouges with the appropriate wood filler and let dry completely. Remove all dust with a wiping cloth. Fill all gaps with a 100% acrylic, siliconized, paintable caulking and allow to dry completely. Patched and filled surfaces should be sanded smooth and dusted clean prior to coating.

Previously Painted Wood: Remove all loose and peeling paint and all other foreign substances. Clean any dirt and grease by scrubbing the surface with a detergent and water solution, followed by a thorough rinsing with clean water. Set nails and fill holes, scratches, and gouges with the appropriate wood filler and let dry completely prior to coating. Remove all dust with a wiping cloth. Fill all gaps with a 100% acrylic, siliconized, paintable caulking, and allow to completely dry prior to coating.

Glossy Surfaces: For maximum adhesion, scuff sand the surface thoroughly before coating.

Weathered Wood Surfaces: To remove loose wood fibers, latex, oil-based and 100% acrylic coatings on new or weathered wood decks, siding, fences, shakes and shingles, use a product such as BEHR PREMIUM® Wood Stain & Finish Stripper No. 64 and follow all label instructions. Use a product such as BEHR PREMIUM All-in-One Wood Cleaner No. 63 and follow all label instructions to clean and brighten the wood surface and to remove light to medium stains caused by mold, mildew, algae and fungus. Be sure to follow all label instructions.

Wood: WARNING! Sanding or scraping pressure treated lumber may be hazardous; wear appropriate protection.

Tannin Bleed & Stainblocking: After priming, test for stain bleed-through by applying the topcoat to a small section. If the stain bleeds through the topcoat, apply a second coat of primer and test again before top-coating the entire area. If bleeding continues, a longer dry time of the primer may be needed before top-coating or an additional coat of primer may be required to block the tannin bleed or stain.

All trademarks, service marks, trade names, and trade dress appearing on this document are the property of their respective owners.

Masonry: Stucco, Concrete, Cut Masonry Unit's (CMUs), Split-Faced Block: New: All masonry surfaces must be cured at least 30 days before painting. The pH must be 10.0 or lower prior to coating. Smooth masonry may require an adequate profile for adhesion. For all other smooth concrete, create a profile using a product with mechanical means.

Masonry: Cement Composition Panels/Siding, Exterior Insulation and Finish Systems (EIFS) or Synthetic Stucco: New: All masonry surfaces must be cured at least 30 days before painting. The pH must be 10.0 or lower prior to coating. All surfaces must be clean, free of dust, chalk, mold and mildew stains, loose and peeling paint and all other foreign substances. Clean surfaces with a detergent and water solution by scrubbing the surface vigorously and rinse with a garden hose or a power washer at a low setting (500-1200 PSI). DO NOT USE HIGH PRESSURE as this may harm the substrate.

PreviouslyPainted Surface: All surfaces must be clean, free of dust,chalk, mold and mildew stains, loose and peeling paint and all other foreign substances. Clean surfaces with a detergent and water solution by scrubbing the surface vigorously and rinse with a garden hose or a power washer and allow to dry.

WARNING! If you scrape, sand or remove old paint, you may release lead dust. **LEAD IS TOXIC.** Contact the National Lead Information Center at 1-800-424-LEAD or log on to www.epa.gov/lead.

RECOMMENDED PRIMER/SYSTEMS

PROPERLY PREPARED NEW SURFACES:

Wood:
BEHR PREMIUM PLUS Interior/Exterior Multi-Surface Primer & Sealer No. 436

BEHR PREMIUM PLUS Interior All-In-One Primer & Sealer No. 75

Tannin/Stainblocking:
BEHR PREMIUM PLUS Interior/Exterior Multi-Surface Primer & Sealer No. 436

For Interior Tannin/Stainblocking: BEHR PREMIUM PLUS Interior All-In-One Primer & Sealer No. 75

Concrete & Masonry:
BEHR PREMIUM Concrete & Masonry Bonding Primer No. 880

BEHR PREMIUM PLUS Interior/Exterior Multi-Surface Primer & Sealer No. 436

BEHR PREMIUM PLUS Interior Stain-Blocking Primer & Sealer No. 75

Masonry with pH Levels up to 13.0:
BEHR PREMIUM Interior/Exterior Basement & Masonry Waterproofer No. 875

BEHR PREMIUM PLUS Interior/Exterior Multi-Surface Primer & Sealer No. 436

CLEAN UP

Clean all tools and equipment with clean water.
For disposal of empty containers and unused product, contact your household refuse collection service.

CAUTIONS/LIMITATIONS

- Reduces surface temperature under intensive sunlight on wood and concrete surfaces when compared to similar colored products made with standard colorants. Temperature reduction can vary based on factors such as color, ambient temperature, time of day, substrate, and the level of direct sunlight the surface receives. Must use BEHR's Heat-Reducing color palette. Caution: Painted surfaces may still remain hot.
- Protect from freezing.
- Do not use on garage floors and driveways.
- Do not use on roofs.
- Two coats are required for optimal coverage, hide, performance and durability.
- For best results, apply at temperatures between 50°F - 90°F. Temperatures above 90°F may affect the application such as drying too fast. Avoid painting in direct sun. NOTE: If the surface is hot to the touch it should be considered too hot to apply this coating.
- Allow 72 hours before subjecting to normal use.
- After 30 days, cured paint film may be cleaned with a mild, non-abrasive liquid detergent.
- Shelf life under normal conditions is two years unopened.

HEALTH & SAFETY INFORMATION

WARNING! IRRITANT. CAUSES EYE AND SKIN IRRITATION. MAY CAUSE RESPIRATORY TRACT IRRITATION. Avoid contact with skin and eyes. Do not breathe dusts, vapor, or spray mist. Sanding, grinding or abrading may release sanding dust, which may be harmful if inhaled and has been shown to cause lung damage or cancer with long term exposure. To avoid breathing in dust, vapors, and spray mist, open windows and doors or use other means to ensure fresh air entry during application, drying, sanding, and/or abrading. If properly used, a respirator (NIOSH approved with particulate pre-filter) may offer additional protection and should be used if adequate ventilation cannot be provided; obtain professional advice before using. If you experience eye watering, headaches, or dizziness during application or drying, increase fresh air or leave the area. Wash thoroughly after handling. Close container after each use.

FIRST AID: If you experience difficulty in breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical assistance immediately. In case of eye contact, flush immediately with plenty of water for at least 20 minutes and get medical attention; for skin, wash thoroughly with soap and water. If swallowed, get medical attention immediately.

This information is provided "as is" and no representations or warranties, either expressed or implied, of merchantability, fitness for a particular purpose or of any other nature are made with respect to this information or to any product referred to in this information. For SDS or to consult with a Behr Paint Company Representative, call 1-800-854-0133 (U.S.A. only) or visit behr.com. ©2025 Behr Process LLC, Santa Ana, CA 92705 U.S.A.