



RUST-OLEUM® HOME FLOOR COATING KITS

DESCRIPTION AND USES

Rust-Oleum® Home Floor Coating is an extremely durable, easy to use, revolutionary technology that allows you to coat over a wide variety of substrates inside the home without stripping, sanding or priming. Transform any room by revamping your outdated floor - simply clean, apply the required Base Coat + Top Coat system for a brand new look to your space.

For use on any bare, stained, sealed or previously coated surfaces such as ceramic tile, porcelain tile, concrete, hard wood, laminate, vinyl and linoleum.

Great for laundry rooms, basements, kitchens, bathrooms, and more.

PRODUCT FEATURES

- 2 Step System
- No stripping, sanding or priming
- Superior adhesion to tough surfaces
- Maximum scratch and stain resistance
- Walk on in one day

PRODUCTS

SKU	DESCRIPTION (Kit)
360098	Home Ultra White/Tint Base Matte Kit
360099	Home Ultra White/Tint Base Semi-Gloss Kit
360100	Home Deep Tint Base Matte Kit
360101	Home Deep Tint Base Semi-Gloss Kit

KIT CONTENTS

- 1-Quart Base Coat
- 1-Quart Top Coat
- 1-4 oz. Cleaner

NOTE: Ultra White Tint Base can be applied as is for White or tinted prior to application. Two base coats are required when applying the Ultra White Tint Base in White. Deep Tint Base must be tinted prior to application.

OTHER SUPPLIES NEEDED (not included in kit)

- 3/8" Nap Roller Sleeve
- 1/4" Nap Roller Sleeve
- Roller Frame
- Roller Pan
- Painter's Tape
- Paint Tray

PRODUCT APPLICATION

READ ALL INSTRUCTIONS CAREFULLY BEFORE STARTING PROJECT

IMPORTANT: All flooring should be tested for adhesion before coating the entire floor. Clean a small 3"x3", inconspicuous area, let dry. Apply base coat over area and allow to dry for 12 hours. Take a utility knife and make an X in the coating down to the flooring. Apply a 4" piece of duct tape over the X and press firmly. Remove the tape with one quick pull. If more than 10% of the coating comes off, the floor will need to be sanded with 60-80 grit sandpaper before coating the entire floor.

SURFACE PREPARATION

Rinse or sweep away any dirt and dust. Clean the entire floor with a cleaner degreaser, such as Original Krud Kutter® Cleaner Degreaser, or provided cleaner. Rinse thoroughly and allow to dry completely. For any areas where caulk is present, caulk needs to be removed before applying coating. For waxed floors, wax needs to be removed before applying coating.

NOTE: Failure to follow this preparation method may result in poor adhesion and possible coating failure.

WARNING! If you scrape, sand or remove old paint from any surface, you may release lead paint dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE; ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

APPLICATION

Rust-Oleum Home Base Coat is ready to use. Do not thin. Stir thoroughly prior to use. If using more than one can of Base Coat, intermix cans together for color uniformity. Apply when air (ambient) temperature is 50-90°F (10-32°C) and relative humidity is below 85%. Use a high quality bristle brush or edger to trim the perimeter and hard-to-reach areas. Use a long handled roller and a high-quality, 3/8" (Base Coat) and 1/4" (Top Coat) nap roller cover to apply an even coat onto the surface.

• TRUSTED QUALITY SINCE 1921 •
RUST-OLEUM®
HOME

RUST-OLEUM® HOME FLOOR COATING KITS

PRODUCT APPLICATION (cont.)

APPLICATION (cont.)

STEP 1: Apply Base Coat in 4'x4' sections, and maintain a wet edge while rolling. Do not let product puddle. Only one coat is recommended, however White requires two coats. After coating the entire floor, wait 6 hours before applying any necessary touch-ups. Let touched-up areas dry for 1-2 hours (dry to touch) and then Top Coat can be applied. If no touch ups are necessary, Top Coat may be applied 6 hours after initial Base Coat application.

STEP 2: Apply Rust-Oleum Home Top Coat in 4'x4' sections, and maintain a wet edge while rolling. Avoid applying too thick and do not let product puddle. Only one coat is recommended. If a second coat is desired for additional durability or uniformity, wait until the first coat is dry to touch (1-2 hours) before applying, but must apply within 24 hours. For vertical application, apply Top Coat in two thin coats. Top Coat must be abraded if recoating after 24 hours. After full system cure of 7 days, if additional coats of Base Coat and Top Coat are desired, simply clean the coated floor, reapply the Base Coat and then reapply the Top Coat.

IMPORTANT: Rust-Oleum Home Base Coat and Top Coat are required for the project.

DRY & TOPCOAT TIMES

For full system, allow 24 hours for light foot traffic. Allow 72 hours before replacing furniture (avoid dragging). Full cure is 7 days. Do not wash before 7 days.

CLEAN UP AND STORAGE

Use water and mild detergent. Dried product can be removed with lacquer/thinner. Protect unused product from freezing. Fully cured floor may be cleaned with mild soap and water after 7 days. Do not use an abrasive cleaner.

LIMITATIONS

Do not use on exterior spaces or garage floors. Do not use on interior surfaces that are sealed with a superhydrophobic sealer. Not for use inside showers. Not food safe.

MAINTENANCE

Fully cured floor may be cleaned with mild soap and water or a general purpose cleaner such as Original Krud Kutter Cleaner Degreaser after 7 days. Do not use an abrasive cleaner.

<small>• TRUSTED QUALITY SINCE 1921 •</small> RUST-OLEUM® HOME	TECHNICAL DATA	ROC-173
RUST-OLEUM® HOME FLOOR COATING KITS		

PHYSICAL PROPERTIES

		STEP 1 BASE COAT	STEP 2 TOP COAT	CLEANER
Resin Type/Composition		Water-based Styrene Acrylic	Water-based Urethane Acrylic	Proprietary Blend of Biodegradable Surfactants, Detergents and Emulsifiers
pH		NA	NA	<12.2
Pigment		Varies with color	Aluminum Oxide, Silica	NA
Solvent		Water, Propylene Glycol	Water, Glycol Ethers	NA
Weight	Per Gallon	10.1-10.6 lbs.	8.63-8.69 lbs	NA
	Per Liter	1.2-1.3 kg	1.03-1.04 kg	NA
Solids	By Weight	47.2-51.2%	29.2-29.3%	NA
	By Volume	36.0-37.3%	27.3-27.6%	NA
Volatile Organic Compounds		<50 g/l	<50 g/l	0%
Recommended Dry Film Thickness (DFT) Per Coat		1.5-2.0 mils	1.0-1.5 mils	NA
Wet Film Thickness (WFT) to Achieve DFT		4.0-5.0 mils	4.0-4.5 mils	NA
Practical Coverage at Recommended DFT		75-100 sq.ft./kit Coverage will vary depending on surface porosity and texture		
Dry Times @ 77° F (25°C) and 50% Relative Humidity	Touch	30-60 minutes	1 hour	NA
	Recoat/Topcoat	6 hours	2 hours	NA
	Foot Traffic	6 hours	24 hours	NA
	Normal Use	NA	72 hours	NA
	Full Cure	7 days		NA
Flash Point		>200°F (93°C)		Non-Flammable
Shelf Life		2 years		NA
Safety Information		For additional information, see SDS		

Calculated values are shown and may vary from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



Rust-Oleum Corporation
 11 Hawthorn Parkway
 Vernon Hills, Illinois 60061

Phone: 866-765-4474
www.rustoleum.com/rohome

Form: ARJ-1992
 Rev.: 031920