




Insulation Jacketing Tape



Backing: Kraft/Scrim/Foil Laminate

Adhesive: Acrylic

Liner: Polycoated Natural Kraft Paper

Colors: White

Specifications: Tested in accordance with UL 723

Standard Sizes: 72mm x 46M

Applications

 Vapor barrier seal for ASJ-faced duct board, pipe insulation, and thermal jacketing Sealing insulation and repairing in cooler/ refrigeration applications

Features Benefits

| • | White Kraft/Scrim/Foil Laminate Backing | • | High strength and tear resistant | |
|---|---|---|--|--|
| | | • | Mold resistant | |
| • | Acrylic Adhesive | • | Low odor adhesive | |
| | | • | Super high tack, aggressive bond to surfaces | |
| • | Low VOC Content | • | Can contribute toward satisfying EQ Credit 4.1 | |
| | | | (Low Emitting Materials) under LEED® | |

Typical Test Values

| | Standard UOM | Metric UOM | Test Method |
|-----------------------|---------------|---------------|-------------|
| Total Thickness | 11.0 mils | 0.279 mm | ASTM D-1000 |
| Adhesion to Steel | 50 oz/in | 5.47 N/cm | PSTC-101 |
| Tensile Strength | 45 lb/in | 78.81 N/cm | ASTM D-1000 |
| Operating Temperature | -35 to 260 °F | -37 to 126 °C | |
| Smoke Developed | 25 | | |
| Flame Spread | 5 | | |
| WVTR | 0.02 perms | | ASTM E96 |
| Emmissivity | 0.03 | | ASTM E408 |
| VOC Content | <1 g/L | | |

Recommended Storage Conditions: 32-90 °F at 50% RH $\pm 2\%$ Standard Shelf Life (at 25C): 36 months from date of manufacture.

The information presented herein was prepared at BERRY PLASTICS CORPORATION (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To Berry Plastics' knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are typical values submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY PLASTICS assumes any legal responsibility.

