## **Surface Application Recommendations**

When used as a stand-alone product, apply the first coat by pouring liquid Lanco® White-Seal™ Plus onto roof and spreading it at a rate of 50 sq.ft/gal. Avoid going twice over the same area. Allow 24 hours before applying subsequent coats.

When used in combination with Polyester Fabric Mesh a base coat of Aqua-Proof MD-863 base membrane must be applied to embed the polyester fabric. Please consult technical data sheet of base membrane for procedures.

**Weather:** Select a warm clear day for installation. Consult weather bureau if needed to ensure there is no forecast of rain. Do not apply product after 4:00PM. Product must be kept rain free for at least 6 hours after application.

Water ponding areas: Areas where water may accumulate for more than 48 hours must be corrected by using roof drains or other means available. If surface level corrections must be made, use Lanco<sup>®</sup> Ultra Level<sup>™</sup> UL-221 self-leveling underlayment or a cement mix with Lanco<sup>®</sup> Concrete Admix-ture CB-4000. See Ultra Level<sup>™</sup> UL-221 product specifications. Important: If used on roofs with slope less than 1/2 inch per foot, warranty will be void if not re-coated annually with one coat of White-Seal<sup>™</sup> Plus.

Repair joints, cracks and seams: Make sure joints, cracks, seams and flashing are clean and dry. With a putty knife, apply Siliconizer™ Crack Filler and a polyester weave over cracks, seams, flashing and around any standing objects about 2 inches to both sides, and let dry thoroughly 24 hours. Lanco Polyflex one-part urethane should be used instead.

**Concrete Roofs:** Repair holes or any weakened areas of concrete surface with good quality masonry cement mix using Lanco® CB4000 Admixture, or Lanco® Bonding Agent CB-900 as per product data applica-tion instructions and let dry. Apply concrete mix and let to cure.

Metal Roofs: Remove rust and prime non-galvanized metals with Lanco® Metal Master Primer™. For galvanized metals, use Lanco® Super Galvanized Primer™ SG-664. Replace loose fasteners. Old fasteners must be covered with Lanco® Siliconizer Elastomeric Crack Filler™ RC-230 or Lanco Polyflex one-part urethane, and let to dry for 24 hours.

Asphalt Membrane and Built-Up Roofs: Remove all loose mineral gravel and clean roof thoroughly. Repair cracks or joints with Lanco<sup>®</sup> Siliconizer Elastomeric Crack Filler™ RC-230 and Lanco<sup>®</sup> Polyester Weave MP-997, apply one coat of Lanco<sup>®</sup> Aqua-Proof™ MD-863 to the entire roof and let dry 24 hours to proceed, apply 4 coats of Lanco<sup>®</sup> White-Seal™ Plus to the entire area. Do not use on pebbles gravel roofs.

## **Method of Application:**

Apply with a Lanco® 3/4" Nap Rough Surface Roller PA-568 or airless spray. Wait 24 hours between coats. Apply only when temperature is above 50°F (10°C). Do not apply if temperature is expected to drop below 50°F (10°C) before the coating has completely dried. Two full coats are generally needed for proper sealing. Always apply coats in different directions. Never thin or dilute from full strength.

**Recommended equipment:** Use an airless pump with pressure of 1,500 to 2,000 psi. A fluid delivery of 1 to 2 gallons per minute with a spray tip of 0.026 to 0.035 will be adequate. Wait 24 hours between coats. The hoses should be at least 3/8" inside diameter and of the high-pressure rate type. If the hose length is more than fifty feet, a larger inside diameter will be required.

**Cleanup:** Clean roller and equipment after use with warm soapy water.

**Drying time:** Approximately 60 minutes to touch. Cure time is controlled by thickness of the applied coating, relative humidity and temperature. Allow 24 hours between coats.

**Limited warranty:** The manufacturers liability in connection with the sale of this product extends only to the replacement price if it should fail to comply with quality standards or specifications. Protect from freezing.

**Warning!:** Do not allow product to freeze. Do not store in temperatures above 105°F. Protective clothing and eyewear should be used during application of this product. Ensure that lid is tight and pail is upright and secure before transporting. Do not allow pail to roll as this may cause lid to loosen and allow leakage to occur. Transport product placed on top of a protective cloth in cargo area of vehicle to prevent damage from accidental spills.

**Cautions:** Contains styrene butadiene and acrylic resin. In case of eye contact, flush thoroughly with water. Do not rub eyes. In case of skin contact, flush area immediately with clean water. If swallowed, do not induce vomiting. Consult a physician immediately. Use only with adequate ventilation. Keep out of reach of children.

<sup>•</sup> CARIBBEAN & SOUTH AMERICA • Urb. Aponte #5, San Lorenzo, Puerto Rico USA 00754 • Tel. (787) 736-4221 Fax (787) 736-5313