



TECHNICAL DATA SHEET
Latex•ite® 10.1 OZ. CRACK REPAIR TUBE
Manufacturer Product#: 42376
UPC#: 090932423763



PHYSICAL PROPERTIES & PERFORMANCE

Appearance: Thick Black Liquid	Maximum VOC: Less than 25 g/l
Application Temperature: 55° F and rising.	Specific Gravity: 1.10
Viscosity: 4,000-7,000 cps	Weight Per Gallon: N/A
Color: Black	Consistency: Black Mastic Asphalt
Boiling Point: 380°	Cure Time (50% relative humidity, 70° F): 24-48 hours.
Freeze ability: Do not allow to freeze.	Container Size & Weight: 10.1 oz. tube

FEATURES

Latex•ite® 10 OZ. CRACK REPAIR TUBE is specially formulated using a combination of pure asphalts and rubber additives to ensure maximum durability and flexibility. It is designed to fill cracks up to 1/2" in width.

- **Fills cracks and joints up to 1/2"**
- **Fills up to 32 feet with 1/4" bead**
- **Fills asphalt cracks and expansion joints**
- **Low VOC Formula / Easy soap & water clean-up**

SURFACE PREPARATION

Latex•ite® 10 OZ. CRACK REPAIR TUBE is a simple and clean process. Before applying the product, it is important to thoroughly clean out the crack and remove any loose debris. Use a screwdriver and whisk broom. Rinsing the crack and allowing it to dry will give you the best results.

APPLICATION

Cracks over 1/2" deep should be filled with solid material to 3/8" from surface before caulking. To apply, cut tip on 45° angle to size of bead desired and puncture inner seal. Apply only to clean, dry surface. Insert tip into cracks forcing patching material well into openings. Do not overfill. Do not use in cracks more than 1/2" wide. Allow to cure prior to sealing. Store in above freezing temperatures. Apply when surface and air temperature are at least 55 degrees F.

PRECAUTIONS

Avoid applying when rainfall is likely within 24 hours of application time. Avoid applying when temperatures drop below 55° F. Allow all repaired surfaces to cure 24 hours prior to sealing. For crack fillers you should wait 24 hours. If the crack filler is firm you may seal over. When transporting this product, ensure that the container is secured. Do not transport on passenger seats or inside the passenger compartment of any vehicle. Protective clothing and eyewear should be used during application.

CLEAN UP & STORAGE

Clean up with mineral spirits and follow with hot, soapy water. Do not heat or store container in temperatures above 110° F. KEEP FROM FREEZING! Product is Non-Hazardous.

!!!CAUTION!!!

Latex•ite® 10.1 OZ. CRACK REPAIR TUBE is for exterior use only. Keep out of reach of children. Keep container capped when not in use. This product contains chemicals known to the state of California to cause cancer and birth defects or other reproductive harm.

Emergency & First Aid Procedures:

Eyes: Immediately flush with clean water for 15 minutes while holding eyelids open; consult a physician.

Inhalation: If overcome by mist or vapor, remove from exposure immediately; call a physician. If breathing is stopped or irregular, start resuscitation, administer oxygen.

Skin: Remove any contaminated clothing and wash skin with soap and warm water. Vegetable or mineral oil can remove dry material.

Ingestion: DO NOT INDUCE VOMITING even though vomiting may occur. If vomiting occurs, keep head below hips to prevent aspiration of liquid into the lungs. Get immediate medical attention.

WARRANTY AND DISCLAIMER

There are no express warranties which extend beyond the description on the face hereof. DALTON ENTERPRISES, INC. DISCLAIMS ANY IMPLIED WARRANTIES OF MERCHANTABILITY, OR OF FITNESS FOR ANY PARTICULAR PURPOSE. Since seller cannot control the manner of use of its products after their sale, seller will not be responsible for any consequential or indirect damages. Rather, seller will, at its options, either replace the goods sold or refund the purchase price. No warranties will apply if the goods are in any way altered or modified after delivery by seller. This warranty does not include labor or cost of labor for the application or consequential damages. This warranty gives you specific rights and you may also have other rights which may vary from state to state.