



# DURALUX<sup>®</sup> URETHANE-ALKYD ENAMEL M720-M774 Series

## 1. BASIC USE AND INFORMATION

DURALUX ENAMEL is a single package, topside enamel for use on primed steel and metal, wood, aluminum or fiberglass. Originally developed for pleasure and commercial boats, the properties of this product also make it ideal for all type onshore or offshore marine maintenance applications. DURALUX ENAMEL is salt water resistant, withstands repeated washings, resists oil and gasoline, and holds up to the discoloration effects of harbor gases.

*Composition:* Urethane modified alkyd

*Limitations:* FOR MARINE RELATED USE ONLY. Do not use on household items, toys, etc.

*Sizes:* 1-gallons and quart containers

*Colors:* Gloss White, Gloss Black, 15 ready-mixed colors

## 2. TECHNICAL INFORMATION

*Recommended Film Thickness:* Dry 2.0 mils. Wet 4.0 mils

*Suggested Spread Rate:* 400 sq. ft. per gallon

*Drying Time:* 1-4 hours, re-coat in 24

*Viscosity:* 75-80 Krebs units

*Thinner:* Mineral spirits or xylene

*60° Gloss:* 85% minimum

*Weight Per Gallon:* 10.04 lbs./gal.

*Solids By Weight:* 64% ± 2%

*Solids By Volume:* 49% ± 2%

*Heat Resistance:* To 300° F

*Freeze-Thaw Stability:* Will not freeze

*Odor:* Mild solvent

*Maximum V.O.C.:* 3.8 lbs./gal.

*Flash Point:* 108° F

## 3. SURFACE PREPARATION

All surfaces must be free of moisture, wax, dirt, rust and other foreign matter. Remove any loose or peeling paint. Use sandpaper, power brushing or a liquid de-glosser to dull any existing gloss. Remove all dust by wiping surfaces with a clean cloth dampened with paint thinner.

**WARNING:** Removal of old paint by sanding, scraping or other means may generate dust or fumes which contain lead. Exposure to lead dust or fumes may cause adverse health effects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as properly fitted and approved (e.g., NIOSH-approved) respirator and proper containment and cleanup. For additional information, contact the USEPA/Lead Information Hotline at 1-800-424-LEAD

*New Steel:* On clean, rust-free steel apply a prime coat of either ZINC-LIKE PRIMER M739, or SUB TROP RED PRIMER M740. Bare galvanized metal should be primed with ALUMINUM BOAT GREEM M736.

*Rusted Or Painted Steel:* Remove all rust, mill scale and dirt by scraping, brushing or sandblasting. Prime surfaces with either ZINC-LIKE M739, YACHT PRIMER M741 or SUB TROP RED M740. Where extensive surface preparation is either impractical or impossible, prepare surfaces by Hand Tool Method SSPC-SP-2 and prime with ALUMITHANE M730.

*Aluminum:* Wipe surface down with white vinegar and prime with either ALUMINUM BOAT PAINT M736 or ZINC-LIKE M739.

*Wood:* Clean dirt and contaminants from the surface. Prime bare wood with YACHT PRIMER M741.

*Fiberglass:* Sand surface until a dull finish is obtained using fine sandpaper or 1/0 steel wool. Topcoat with two full coats of DURALUX.

## 4. APPLICATION

Apply two coats of DURALUX on properly prepared surfaces. "Feather edge" last brush strokes to insure a smooth finish. Do not over apply. Maintain a wet edge to avoid lap marks.

*Method of Application:* Brush, roller or spray. For airless spray use a .013" to .019" orifice with 1,850 psi at tip. For conventional spray use Graco 700 Gun 217-757 equipment or equivalent, with fluid pressure of 20 lbs. and atomizing pressure of 35-40 lbs.

*Thinning:* Not recommended. If thinning is desired, use PAINT THINNER 650 or xylene not to exceed a half pint per gallon.

*Clean Up:* Immediately after use with mineral spirits or xylene.

*Precautions:* Combustible. Dangerous if consumed. Avoid breathing vapor or spray. Avoid contact with eyes. Use in well ventilated areas. MSD Sheet available upon request.

## 5. MAINTENANCE

Painted surfaces may be cleaned with detergents, oil or grease emulsifiers or pressure washers.

## 6. GUARANTEE

Standard warranty

## 7. TECHNICAL SERVICE

Duralux Marine Paint representative  
504-340-3359

## 8. INFORMATION ONLINE

[www.duraluxpaint.com](http://www.duraluxpaint.com)