



## BEHR PREMIUM® Solid Color Concrete Stain

No. 800 White Base  
No. 830 Deep Base

- Interior/Exterior
- Decorative, Flat Finish
- Siliconized 100% Acrylic
- Chemical and Hot-Tire Resistant
- Available in Custom Colors



**Spread Rate:**  
Rough 400-500 Sq. Ft.  
Smooth 500-600 Sq. Ft.



**Dry Time:**  
1 Hr. Dry to Touch.  
4 Hr. Recoat



**Clean-Up:**  
Soap & Water



**Protect**  
from Freezing

**CAUTION:** Painted surfaces may become slippery when wet. Adding a non-skid floor additive may help prevent slipping.

### WHERE TO USE

Properly prepared Interior/Exterior surfaces such as: Concrete, Masonry Walls, Basements Floors, Patios, Walkways, Driveways\*, Garage Floors\*, Pool Decks\*\*, Tennis Courts, Cement Blocks, Pillars and Brick. Not for use on surfaces subject to hydrostatic pressure.

\* Driveways and Garage Floors - Lack of proper surface preparation and/or over-application can lead to automobile tires lifting the product from the surface. \*\* Light and pastel colored concrete stains should be used over pool deck surfaces. DARK COLORS RETAIN HEAT.

### PREPARATION † (Proper Surface Preparation is Required.)

- All surfaces must be clean, sound, dry and free of any dirt, oil and grease.
- **New and Uncoated Concrete or Masonry Surfaces:** Allow new surfaces to cure 30 days. Clean and etch surface using a product such as a muriatic acid etcher (read and follow all manufacturer's label directions) to achieve a textured profile similar to 150 grit sandpaper. Wipe your fingers over the clean, dry floor to check for dust or powder. Ensure there is no residue on your fingers that may have been left from the etcher. If residue is found, rinse the surface to remove residue. Allow the surface to dry completely. Sprinkle a few drops of water onto the surface. If water is quickly absorbed and the surface feels like 150 grit sandpaper, the surface is ready. If not, re-etch. Apply a product such as BEHR PREMIUM® No. 880 Concrete & Masonry Bonding Primer to increase adhesion of topcoat to the surface.
- **Painted, Stained or Sealed Concrete:** For a painted surface in sound condition, use a product to clean and prepare the surface. If the coating is failing or peeling, use a paint stripper to remove old coating or scrape/sand down to a sound concrete surface. Scuff sand glossy surfaces. Clean and spot etch any exposed concrete using a product such as a muriatic acid etcher (read and follow all manufacturer's label directions) to achieve a textured profile similar to 150 grit sandpaper. Remove all dust with a damp cloth, allow to dry. Spot prime all bare concrete areas with a product such as BEHR PREMIUM No. 880 Concrete & Masonry Bonding Primer to increase adhesion of topcoat to the surface.

### APPLICATION

- Intermix all cans of same product to ensure color uniformity.
- Stir stain before and occasionally during application. Use product when air and surface temperatures are between 50-90° F (10-32° C).
- Apply a thin, even coat using a 1/4- 3/8" nap roller cover, pad applicator, nylon/polyester brush or an airless sprayer with an adjustable tip (.015"- .019", 60 mesh filter).
- Use long, even strokes in one direction to avoid lap lines.

- Spread rate varies, depending on the surface texture, porosity and application method. Do not thin if using a roller or brush; however, if using a sprayer and thinning is required, thin with water at a rate of no more than 1/2 pint per gallon.
- Additional coats may be required for optimal hide and durability. Periodic touch-ups may be necessary.

### DRY TIME

- Longer dry time required in cooler temperatures and higher humidity. Allow 24 hours for light foot traffic.
- Allow 72 hours before subjecting surface to automotive tires, repositioning planters or furniture. Park tires on corrugated cardboard for 14 days after applying stain.
- After 30 days, dry stained surface may be cleaned with a mild, non-abrasive liquid detergent.

### DISPOSAL

- Properly dispose of all soiled rags. To recycle or properly dispose of product in your community, contact your household refuse collection service.

### LIMITED WARRANTY

Visit [behr.com/warranty](http://behr.com/warranty) or call 1-800-854-0133 Ext. 2 for more information.

† **WARNING!** If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. Contact the National Lead Information Center at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

**WARNING** Cancer and Reproductive Harm [www.P65Warnings.ca.gov](http://www.P65Warnings.ca.gov)

**WARNING! CAUSES EYE AND SKIN IRRITATION. MAY CAUSE RESPIRATORY TRACT IRRITATION. CONTAINS: ETHYLHEXYL BENZOATE, 1-METHYL-2-PYRROLIDONE AND CRYSTALLINE SILICA.** Avoid contact with skin and eyes and avoid breathing vapors, spray mist and sanding dust. Sanding, grinding or abrading may release sanding dust, which may be harmful if inhaled and has been shown to cause lung damage or cancer with long term exposure. Do not breathe dusts, vapor, or spray mist. To avoid breathing in dust, vapors, and spray mist, open windows and doors or use other means to ensure fresh air entry during application, drying, sanding, and/or abrading. If properly used, a respirator (NIOSH approved with particulate pre-filter) may offer additional protection and should be used if adequate ventilation cannot be provided; obtain professional advice before using. If you experience eye watering, headaches, or dizziness during application or drying, increase fresh air or leave the area. Avoid contact with eyes and skin. Wash thoroughly after handling. Close container after each use. **FIRST AID:** If you experience difficulty in breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical assistance immediately. In case of eye contact, flush immediately with plenty of water for at least 20 minutes and get medical attention; for skin, wash thoroughly with soap and water. If swallowed, get medical attention immediately. **CAUTION: KEEP OUT OF REACH OF CHILDREN - DO NOT TAKE INTERNALLY.**



©2021 Behr Process Corporation  
Santa Ana, CA 92705 U.S.A. • [behr.com](http://behr.com)  
V.O.C. (C.O.V.) <100 g/L • REV. 06/21