

• TRUSTED QUALITY SINCE 1921 •
RUST-OLEUM®
 SPECIALTY

RUST-OLEUM® SPECIALTY CAMOUFLAGE PAINT

DESCRIPTION AND USES

Rust-Oleum® Specialty Camouflage paints provide a non-reflective finish for hunting and sporting equipment. Tough, chip-resistant finish is ideal for indoor and outdoor projects. Various colors can be combined in a variety of patterns to blend with any terrain. Ideal for use on vehicles, tree stands, decoys, blinds, boats and equipment.

For a real life pattern, use leaves and twigs as stencils. Apply a base coat of color. Lay the leaves and twigs randomly over the object you are painting. Brush over the items using three or more colors.

PRODUCTS

SKU	DESCRIPTION (32 Oz. Quart)
379558	Camouflage Black
379559	Camouflage Earth Brown
379560	Camouflage Deep Forest Green
379561	Camouflage Army Green
379562	Camouflage Khaki

PRODUCT APPLICATION

READ ALL INSTRUCTIONS CAREFULLY BEFORE STARTING PROJECT.

SURFACE PREPARATION

Remove loose paint and rust with wire brush or sandpaper. Lightly sand glossy surfaces. Clean with soap and water, rinse and let dry.

WARNING! If you scrape, sand or remove old paint from any surface, you may release lead paint dust. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE; ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

PRIMING

Use of a Painter's Touch® primer provides superior adhesion and hiding and is especially recommended for bare wood and metal. To apply a top coat, follow recoat times on primer.

PRODUCT APPLICATION (cont.)

APPLICATION

Use outdoors or in a well-ventilated area such as an open garage. Use when temperature is between 50°F (10°C) and 90°F (32°C) and humidity is below 85% to ensure proper drying.

PAINTING

Stir thoroughly. Thinning is not required. In hot, dry conditions, you may thin with up to 2-oz. water per quart to extend dry time. Avoid painting in direct sunlight or on hot surfaces. Use a good synthetic brush (roller application not recommended). Avoid excessive brushing as this will reduce film thickness and protection. Use light, even strokes to ensure an even flow and the smoothest finish.

DRY AND RECOAT TIMES

Based on 77°F (25°C) and 50% relative humidity. Allow more time at cooler temperatures. Dries to the touch in 30 minutes, to handle in 1 hour and fully dry in 2-4 hours. May be recoated after 2-4 hours.

CLEAN UP

Clean brush and other application tools immediately with soap and water.

PROTECT FROM FREEZING.

• TRUSTED QUALITY SINCE 1921 • RUST-OLEUM® SPECIALTY	TECHNICAL DATA	SPC-120
RUST-OLEUM® SPECIALTY CAMOUFLAGE PAINT		

PHYSICAL PROPERTIES

		CAMOUFLAGE PAINT
Resin Type		Water-based Acrylic
Weight Per Gallon		9.10-9.62 lbs.
Solids	By Weight	37-42%
	By Volume	30-33%
Volatile Organic Compounds		<340 g/l
Recommended Dry Film Thickness (DFT) Per Coat		1.5-2.5 mils (37.5-62.5µ)
Wet Film to Achieve DFT (unthinned material)		5.0-6.0 mils (125-150µ)
Practical Coverage at Recommended DFT (assumes 15% material loss)		50-90 sq. ft./quart (1.0-2.2 m ² /l)
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Touch	30 minutes
	Handle	1 hour
	Recoat	After 2-4 hours
	Full Cure	7 days
Shelf Life		5 years
Dry Heat Resistance		200°F (93°C)
Safety Information		For additional information, see SDS

Calculated values are shown and may vary from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



Rust-Oleum Corporation
 11 Hawthorn Parkway
 Vernon Hills, Illinois 60061

Phone: 800-837-8677
www.rustoleum.com

Form: ARJ-2303
 Rev.: 080122