SRT-04



STOPS RUST SATIN BRUSH

DESCRIPTION AND USES

Rust-Oleum[®] Stops Rust[®] Satin Finish provides a classic low sheen and durable finish. This smooth, protective enamel offers excellent coverage, chip resistance and color retention. Use on interior/exterior metal or wood surfaces. For even longer, lasting protection, use a Stops Rust[®] primer first. Not for use on galvanized steel.

PRODUCTS

SKU (1-Quart)	Description
242110	Dark Olive
242111	Dark Taupe
242112	Old Brick
242113	Dark Brown
7732502	Hunter Green
7767502	Redwood
7774502	Chestnut Brown
7777502	Black
7791502	White
7793502	Shell White

PRODUCT APPLICATION

PAINTING CONDITIONS

Apply only when air and surface temperatures are between 50-90°F (10-32°C) and humidity is below 85% to ensure proper drying. Do not apply to surfaces that will exceed 200°F (93°C). Do not use on galvanized steel.

SURFACE PREPARATION

ALL SURFACES: Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with a commercial detergent or other suitable cleaning method. Rinse thoroughly with fresh water and allow to fully dry. All surfaces must be dry at time of application.

STEEL: Scrape and wire brush or power tool clean to remove loose rust, scale and deteriorated previous coatings. Use 7769 Rusty Primer for sound rusted or clean metal before application of a finish coat. 7780 White Clean Primer is best for clean metal but may be used on sound rusted metal as well.

PRODUCT APPLICATION (cont.)

PREVIOUSLY COATED: Previously coated surfaces must be sound and in good condition. Smooth, hard, or glossy finishes should be scarified by sanding to create a surface profile. The Stops Rust Satin Finish is compatible with most coatings, but a test patch is suggested. WARNING! If vou scrape, sand or remove old paint from any surface. vou may release lead paint dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE; ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

APPLICATION

Before using, stir thoroughly to ensure any settled pigment is re-dispersed. If necessary, thin the material with acetone. For brush or roller, thinning is not normally required. For air spray, thin up to 15% with acetone. Do not thin with gasoline, lacquer thinner, turpentine, etc. For airless spray, thinning is not normally required. Apply with a good quality brush, roller or spray gun.

Brush: Use light, even strokes. Excessive brushing reduces film thickness and protection.

Roller: A 3/8" nap roller should be used on rough surfaces. Cover approximately one square yard at a time. Roll away from previously coated area and work back to it for a uniform appearance. Use a brush on crevices and sharp edges.

Spray Gun: Follow spray gun directions carefully. Always keep the gun ten to twelve inches from the surface and in motion while spraying.

CLEAN-UP

Clean brush and tools with Mineral Spirits.

TECHNICAL DATA

RUST-OLEUM STOPS RUST SATIN BRUSH

PHYSICAL PROPERTIES

		SATIN BRUSH FINISHES	
Resin Type		Oil modified alkyd	
Pigment Type		Varies with color	
Solvents		Mineral Spirits	
Weight	Per Gallon	9.2-10.2 lbs	
	Per Liter	1.1-1.2 kg	
Solids	By Weight	59.6-64.0%	
	By Volume	42.2-43.0%	
Volatile Organic Compounds		<445 g/l	
		(3.72 lbs./gal.)	
Recommended Dry Film		1.5-2.5 mils	
Thickness (DFT) Per Coat		(37.5-62.5µ)	
Wet Film to Achieve DFT		3.5-6.0 mils	
		(87.5-150µ)	
Theoretical Coverage at 1 mil DFT (25µ)		169-173 sq.ft./qt.	
		(16.6-17.0 m ² /l)	
Practical Coverage at Recommended DFT		60-100 sq.ft./qt.	
		(5.9-9.8 m ² /l)	
Dry Times at 70°F (21°C) and 50% Relative Humidity	Touch	2-4 hours	
	Handle	5-9 hours	
	Recoat	After 24 hours	
Dry Heat Resistar	nce	200°F (93°C)	
Shelf Life		5 years	
Flash Point		104°F (40°C)	
Safety Information		For additional information, see MSDS	

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



Rust-Oleum Corporation 11 Hawthorn Parkway Vernon Hills, Illinois 60061 An RPM Company³/₅

Phone: 877•385•8155 www.rustoleum.com Form: CS2157 Rev.: 022813