



Spray Specification for The Home Depot – DRYLOK® EXTREME

For best results DRYLOK® Extreme should be well stirred and sprayed at room temperature (70°F and 60% relative humidity). Conditions of high humidity and/or low temperature can cause poor results. It is recommended that a small test area be done before beginning the project. Please refer to DRYLOK Extreme Data sheet for additional product information.

Spray Recommendation:

Graco Magnum ProX21 Cart Airless Paint Sprayer

- Graco Model #17G182; Internet #206729605

Graco Magnum ProX21 Stand Airless Paint Sprayer

- Graco Model #17G181; Internet #206729589

Remove Gun filter prior to spraying. Use Graco RAC IV 621 tip (Graco P/N 221621; Internet#300876937). Spray pressure 2200 to 2500 psi. Hold gun twelve inches from surface when spraying. Spray cross hatching patterns (North/South then East/West) with two coats building to a 14 to 16 wet mil thickness. First coat, back roll with $\frac{3}{4}$ " nap or back brush to fill any pinholes or pores in masonry. Allow to dry 4 hours before applying second coat. Repeat first coat procedure.

For Commercial Applications:

Graco Pro210ES Hi-Boy Airless Paint Sprayer

- Graco Model #17C305; Internet #205841124

Graco Pro210ES Airless Paint Sprayer

- Graco P/N 17D163; Store SKU #1001263425; Internet #205851162

Remove Gun and Manifold filters prior to spraying. Use Graco RAC IV 621 tip (Graco P/N 221621; Internet #300876937). Spray pressure 2200 to 2500 psi. Spray cross hatching patterns (North/South then East/West) with two coats building to a 14 to 16 wet mil thickness. First coat, back roll with $\frac{3}{4}$ " nap or back brush to fill any pinholes or pores in masonry. Allow to dry 4 hours before applying second coat. Repeat first coat procedure.

REV 2.28.18