BARN & FENCE PAINT

NO. 35 BARN WHITE

PRODUCT INFORMATION

BEHR® Barn & Fence Paint is an exterior paint combining the best features of oil and latex for superior color retention, adhesion, penetration and durability. Dry film will not harm livestock.

RECOMMENDED USES:

Use on properly prepared exterior vertical surfaces such as smooth or rough sawn wood.

PRODUCT SPECIFICATIONS:

Tint Bases/Max Tint Load:
No. 35 Barn White
No. 25 Barn Red

Sheen: 0 – 5 @ 85°

Resin Type: Oil Latex

Weight per Gallon: 11.1 lb

% Solids by Volume: 35% ± 2%

% Solids by Weight: 49% ± 2%

VOC: < 50 g/L

Flash Point: N/A

Viscosity: 87 – 93 KU

Recommended Film Thickness:
Wet: 8.0 mils / Dry: 2.8 mils @ 200 sq ft/gal
Wet: 3.2 mils / Dry: 1.1 mils @ 500 sq ft/gal

Coverage: 200 – 500 sq ft/gal, depending on application method and substrate porosity. Does not include the loss of material from spraying.

APPLICATION:

Brush: Nylon/polyester

Roller: 3/8" – 3/4" nap roller cover, depending on surface texture

Airless Spray:
Tip: .015"- .019"
Filter: 60 mesh

Thinning: If required, thin with water at a rate of no more than 1/2 pint per gallon.

Dry Time: @ 77° & 50% RH
To Touch: 2 – 3 hours
To Recoat: 6 – 8 hours
Longer dry time may be required in cooler temperatures and higher humidity.

SURFACE PREPARATION:

All surfaces must be clean, free of dust, chalk, oil, grease, wax, polish, mold and mildew stains, loose and peeling paint, rust, and all other foreign substances.

New, weathered, pressure-treated or uncoated wood: If wood fibers or debris are pulled onto the tape, the wood surface is not sound and additional preparation is required as follows: Clean surface with a product such as BEHR PREMIUM NO. 64 Wood Stain & Finish Stripper. Rinse. Follow with a product such as BEHR PREMIUM NO. 63 All-In-One Wood Cleaner at full strength to remove mill glaze and/or loose wood fibers, dirt and other debris. Rinse and allow to dry.

Previously painted, stained or clear sealed wood: Sand all glossy surfaces. If surface is in good condition, apply directly over clean, dry surface. If the latex or oil-based finish has started to crack, peel or flake, use a product such as BEHR PREMIUM® Wood Stain & Finish Stripper No. 64 on wood to remove the coating. Rinse thoroughly. Follow with a product such as BEHR PREMIUM All-In-One Wood Cleaner No. 63. Scrub, rinse, and allow to dry completely.

WARNING If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Center at 1-800-424-LEAD or log on to www.epa.gov/lead.

SYSTEM RECOMMENDATIONS:

Wood:
- 1 coat BEHR® Multi-Surface Interior/Exterior Stain-Blocking Primer & Sealer No. 436
  2 coats BEHR® Barn & Fence Paint

COMPLIES WITH THE BELOW AS OF 2/1/2024			
SCAQMD	YES	LADCO	YES
CARB SCM 2007	YES	AIM	YES
OTC Phase II	YES	MPI	16
OTC	YES		

CLEAN-UP/DISPOSAL:

Clean all tools and equipment with warm, soapy water. Do not dispose of this product down a drain. If spilled, contain material and remove with an inert absorbent. Dispose of contaminated absorbent, container and unused product in accordance with all current federal, state and local regulations. For recycling or disposal of empty containers, unused product and soiled rags, contact your household refuse collection service.

CAUTIONS/LIMITATIONS:

- Protect from freezing.
- Do not use on horizontal surfaces subject to foot traffic.
- For best results, apply when air, material and surface temperatures are between 50°F and 90°F. Temperatures above 90°F can cause the paint to dry too fast, whereas temperatures below 50°F can inhibit proper film formation. Avoid applying in direct sun.
- Allow two weeks before washing or cleaning for full cure.
- Shelf life under normal conditions is two years unopened.

This information is provided "as is" and no representations or warranties, either express or implied, of merchantability, fitness for a particular purpose or of any other nature are made with respect to this information or to any product referred to in this information. For SDS or to consult with a Behr Paint Company representative, call 1-800-854-0133 or visit behr.com. ©2024 Behr Process Corporation, Santa Ana, CA 92705 U.S.A.

Revised 02/2024

BARN & FENCE PAINT

NO. 35 BARN WHITE

GENERAL INFORMATION:

WARNING IRRITANT. CAUSES EYE AND SKIN IRRITATION. MAY CAUSE RESPIRATORY TRACT IRRITATION. Avoid contact with skin and eyes. Do not breathe dusts, vapor, or spray mist. Sanding, grinding or abrading may release sanding dust, which may be harmful if inhaled and has been shown to cause lung damage or cancer with long term exposure. To avoid breathing in dust, vapors, and spray mist, open windows and doors or use other means to ensure fresh air entry during application, drying, sanding, and/or abrading. If properly used, a respirator (NIOSH approved with particulate pre-filter) may offer additional protection and should be used if adequate ventilation cannot be provided; obtain professional advice before using. If you experience eye watering, headaches, or dizziness during application or drying, increase fresh air or leave the area. Wash thoroughly after handling. Close container after each use.

FIRST AID: If you experience difficulty in breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical assistance immediately. In case of eye contact, flush immediately with plenty of water for at least 15 minutes and get medical attention; for skin, wash thoroughly with soap and water. If swallowed, get medical attention immediately.

KEEP OUT OF REACH OF CHILDREN – DO NOT TAKE INTERNALLY.

This information is provided "as is" and no representations or warranties, either express or implied, of merchantability, fitness for a particular purpose or of any other nature are made with respect to this information or to any product referred to in this information. For SDS or to consult with a Behr Paint Company representative, call 1-800-854-0133 or visit behr.com. ©2024 Behr Process Corporation, Santa Ana, CA 92705 U.S.A.

Revised 02/2024