



Spec Sheet – 3-Bar Rebar Stand

TYPICAL RESIN PROPERTIES			
	ASTM TEST METHOD	VALUE	UNIT
MELT FLOW RATE:	D1238	18	G/10 min
DENSITY	D1505	0.900	G/CM3
TENSILE	D638	3,200	PSI
FLEXURAL MODULUS	D790	145,000	PSI
DEFLECTION TEMP	D648	180	F
HARDNESS VALUE	R-Scale	65	
<u>STRENGTH</u>			
	VALUE	UNIT	
MAXIMUM LOAD	665	LBS/PER BAR	

<u>PRODUCT SPECIFICATIONS</u>		
	VALUE	UNIT
REINFORCEMENT GROUND CLEARANCE	3	IN
OVERALL HEIGHT	3-5/8	IN
CHAIR BASE DIMENSIONS	14-1/2 x 5-1/2	IN
BAR SPACING	5	IN
CHAIR WEIGHT	.30	LBS
REINFORCEMENT BAR SIZE	#4 & #5	