



Architectural Coatings

PPG SPEEDHIDE Interior MaxPrime™ Latex Primer/Surfacer

GENERAL DESCRIPTION

Our best professional high build interior latex primer formulated to meet the performance requirements of professional applicators. SPEEDHIDE Interior MaxPrime Latex Primer/Surfacer ensures the finish will be a smooth and uniform sheen by minimizing the differences in both porosity and texture between drywall paper and joints. It also minimizes drywall imperfections such as minor sanding grooves, pinholes, and nicks. Recommended for use on properly prepared interior gypsum wallboard-drywall.

TINTING AND BASE INFORMATION

Refer to the appropriate color formula book, automatic tinting equipment, and or computer color matching system for color formulas and tinting instructions.

6-4 White

RECOMMENDED SUBSTRATES

Gypsum Wallboard-Drywall

PRODUCT DATA

PRODUCT TYPE: Vinyl Acrylic Latex
SHEEN: Flat
VOLUME SOLIDS: 26% +/- 2%
WEIGHT SOLIDS: 44% +/- 2%
VOC: <50 g/L (0.4 lbs./gal.)

WEIGHT/GALLON: 11.0 lbs. (5.0 kg) +/- 0.2 lbs. (91 g)

COVERAGE: Approximately 400 sq. ft./gal. (37 sq. m/3.78L) per U.S. Gallon (3.78L) on smooth, nonporous surfaces.

Wet Film Thickness: 4.0 mils
Wet Microns: 101.6
Dry Film Thickness: 1.0 mils
Dry Microns: 25.4

Coverage figures do not include loss due to surface irregularities and porosity or material loss due to application method or mixing.

DRYING TIME: Dry time @ 77°F (25°C); 50% relative humidity.

To Touch: 30 minutes
To Recoat: 1 hour

Drying times listed may vary depending on temperature, humidity, film build, color, and air movement.

CLEANUP: Clean tools with warm soapy water

DISPOSAL: Contact your local environmental regulatory agency for guidance on disposal of unused product. Do not pour down a drain or storm sewer.

FLASH POINT: Over 200°F (93°C)

CONFORMANCE STANDARDS

- VOC compliant in all regulated areas
Can help earn LEED® 2009 credits

APPLICATION INFORMATION

Stir thoroughly. When using more than one can of the same color, intermix to ensure color uniformity. USE WITH ADEQUATE VENTILATION. KEEP OUT OF REACH OF CHILDREN. Read all label and Material Safety Data Sheet (MSDS) information prior to use. MSDS are available through our website or by calling 1-800-441-9695.

Application Equipment: Apply with a high quality brush, roller, paint pad, or by airless spray equipment. Where necessary, apply a second coat.

Airless Spray: Pressure 2000 psi, tip 0.015" - 0.021"
Spray equipment must be handled with due care and in accordance with manufacturer's recommendation. High-pressure injection of coatings into the skin by airless equipment may cause serious injury.

Brush: Polyester/Nylon Brush
Roller: 3/8" - 3/4" nap roller cover

Thinning: Thinning is not usually required. If necessary, thin with up to 1/4 pint (118mL) of water per U.S. gallon (3.78 L) of paint.

Permissible temperatures during application:

Table with 3 rows: Material (50 to 90°F / 10 to 32°C), Ambient (50 to 100°F / 10 to 38°C), Substrate (50 to 100°F / 10 to 38°C)

FEATURES / BENEFITS

Features

- Provides a uniform base
Great hiding
User friendly
Fast drying
Easy to sand
Easy soap and water clean up
Can help earn LEED 2009 credits

Benefits

- Eliminates flat and shiny spots
Hides minor surface imperfections
Broad application utility
Saves time with quick recoat
Saves labor
No solvent disposal issues
Contributes to sustainable design

GENERAL SURFACE PREPARATION

Surfaces to be coated must be dry, clean, sound, and free from all contamination including loose and peeling paint, dirt, grease, oil, wax, mildew, rust, product fines, and dust. Remove loose paint by wire brushing, scraping, or sanding. Putty all nail holes and caulk all cracks and open seams. Sand all glossy, rough, and patched surfaces. Feather back all rough edges to sound surface by sanding.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust or fumes. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST OR FUMES CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a properly fitted NIOSH-approved respirator and prevent skin contact to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the USEPA National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead. In Canada contact a regional Health Canada office. Follow these instructions to control exposure to other hazardous substances that may be released during surface preparation.

GYPSUM WALLBOARD-DRYWALL: Nails or screws should be countersunk, and they along with any indentations should be mudded flush with the surface, sanded smooth and cleaned to remove any dust prior to painting the substrate.

LIMITATIONS OF USE

Apply when air, surface and product temperatures are above 50°F (10°C). Due to the porosity of this primer/surfacers, two coats of pearl, satin, or semi-gloss topcoat will be necessary to achieve the full sheen of the topcoat. When topcoating with a flat sheen, only one coat is required.

Not recommended for use on floors.

PROTECT FROM FREEZING.

PACKAGING

1-Gallon (3.78 L)
5-Gallon (18.9 L)

The PPG logo is a registered trademark of PPG Industries Ohio, Inc. *SPEEDHIDE* is a registered trademark and *MaxPrime* is a trademark of PPG Architectural Finishes, Inc. *LEED* is a registered trademark of the US Green Building Council.

PPG Architectural Finishes, Inc. believes the technical data presented is currently accurate; however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, visit our web site or call 1-800-441-9695.



PPG Industries, Inc.
Architectural Coatings
One PPG Place
Pittsburgh, PA 15272
www.ppgpittsburghpaints.com
www.ppgporterpaints.com

Technical Services
1-800-441-9695
1-888-807-5123 fax

Architect/Specifier
1-888-PPG-IDEA

PPG Canada, Inc.
Architectural Coatings
4 Kenview Blvd
Brampton, ON L6T 5E4

A1.17 4/2013
(Supersedes 1/2012)

Made in the
USA