



Physical Property	Typical Value	Test Method
Appearance	Black liquid with silver pigment	-
Solids by Weight	52% minimum	ASTM D2824
Solids by Volume	43% minimum	ASTM D2697
VOC	400 g/l maximum	EPA Method 24
Weight per Gallon	7.7–8.3 lbs.	ASTM D2828
Brookfield Viscosity	4,000–7,000 cPs	ASTM D2828
Tensile Strength Film, Initial	135 psi minimum	ASTM D2370
Solar Reflectance per CRRC	0.53 initial and 0.42 after 3 years	ASTM C1549
Thermal Emittance per CRRC	0.50 initial and 0.56 after 3 years	ASTM C1371
Solar Reflectance Index (SRI) per CRRC	48 initial and 33 after 3 years	ASTM E1980
Aluminum Content	>9%	-
Water Content	0.3 maximum	-
Flash Point	105 °F (40 °C) minimum	ASTM D3278
Application Temperature (Ambient)	40 °F (4 °C) and rising	-

#### Approvals and Certifications

- ENERGY STAR<sup>®</sup> Certified
- Cool Roof Rating Council (CRRC) Rated Product: Product ID# 0620-0040
- Meets or exceeds ASTM D2824, Standard Specification for Aluminum-Pigmented Asphalt Roof Coatings, Type III

#### Description

**Henry<sup>®</sup> 555 Fibered Aluminum Roof Coating** is a premium fibered aluminum coating that forms a tough, reflective, weathering surface. It can help decrease air conditioning costs by reducing heat transfer through the roof.

#### Features

- Two-in-one benefits:
  - Water-resistant
  - Stops rust on metal roofs
- Seals hairline cracks and pinholes
- >50% solar reflectance per ASTM D2824, Type III

#### Product Size

1 gallon, 5 gallon

#### Usage

- Recoating roofs previously coated with asphalt emulsion or aluminum coatings
- Asphalt roofs, including Built-Up Roofing (BUR) and Modified Bitumen (MB)
- Metal roofs

## Henry® 555 Fibered Aluminum Roof Coating

---

### Application

---

**Clean:** Before coating the roof, use a pressure washer or high pressure nozzle and water hose to wash the roof with a non-filming detergent, such as TSP or TSP substitute. Use appropriate pressure and take caution not to inject water into the roofing substrate. In areas with stubborn dirt, grease or other contaminants, use a stiff bristle brush or broom to scrub the areas clean with additional water and non-filming detergent. Treat algae or moss. The most effective method of cleaning algae and moss from a roof is with a 50:50 mix of laundry strength liquid chlorine bleach and water. Apply with a sprayer and allow the solution to dwell on the roof surface for 15 to 20 minutes, and then rinse thoroughly with low pressure water. Extended dwell times may be necessary. However, avoid letting the solution dry completely as this may prevent complete rinsing. Take proper precautions to protect landscaping and surrounding areas from the chlorine bleach solution. Use appropriate personal protective equipment when working with chlorine bleach. In severe cases, it may take more than one bleach treatment to kill all of the moss. Give the roof a final rinse to ensure it is free of all detergent or anything else that could affect adhesion. Allow roof to dry completely before application. Using a leaf blower or broom, clear any remaining dust, dirt, debris or foreign material that may prevent proper adhesion.

**Prep:** Carefully inspect area to be coated, including around pipes, chimneys, equipment, roof edges and walls. Repair all cracks, breaks, splits and holes by embedding Henry® 181 or 183 Roof Repair Fabric between two heavy coats of Henry® 209XR, 208R® or 208® Wet Patch® Roof Leak Repair, Henry® 505 FlashMaster™ Flashing Cement or Henry® 204® Plastic Roof Cement, applied over and at least 2" beyond repair. Allow mastic to cure 30 days before coating. Ensure all drains are clean and clear, and cut back any vegetation that is growing that may cause debris to fall on the roof and clog drains in the future. On metal roofs, remove rust by wire brushing.

**Optional:** Apply a base coat of Henry® 107® Asphalt Emulsion Sealer and Dampproofers at a rate of 3-4 gallons per 100 square feet. Emulsion base coat must be fully cured before applying reflective coating; usually in 3-7 good drying days.

**Apply:** Mechanically mix thoroughly before and during application. Apply to a dry surface. Application to a damp surface will cause this product to appear brown. Apply with good quality, soft bristled brush, or commercial grade spray equipment. Apply liberally, brushing in one direction only. Do not lap. Over brushing will interfere with leafing action of the aluminum. Care should be taken to coat at a consistent coverage rate. Failure to continuously mix product before and during use, inconsistent coverage rates or applying in multiple directions hinders the leafing action of the aluminum and may lead to varying shades of color when the product dries.

**DO NOT THIN.** DO NOT APPLY IF RAIN OR TEMPERATURES BELOW 40 °F (4 °C) ARE EXPECTED WITHIN 12 HOURS (low temperature and/or high humidity may require longer drying time). Do not heat container or store at temperatures greater than 110 °F (43 °C). When transporting, make sure the pail is secured and the lid is tight to prevent spills. CLOSE AIR INTAKES ON ROOF UNTIL SOLVENTS DISSIPATE! This coating is not intended for application over rubber or PVC sheet roofs, SPF roofs, silicone coated roofs, shingles of any kind or roofs previously covered with loose or embedded gravel ballast.

**Ponding Water:** Discoloration is normal and to be expected in ponding water areas. Discoloration of the coating does not hinder its ability to protect the underlying surface and is only cosmetic in nature.

### Coverage

---

Approximately 240-320 square feet per 5 gallon size pail (approximately 100 square feet per 1.25-2.0 gallons). Coverage varies with surface texture. As roof slope increases, coverage rate should be reduced to prevent run off or slippage.

### Clean-up

---

Clean tools with mineral spirits. Clean hands with waterless hand cleaner.

**Limited Product Warranty**

---

We, the manufacturer, warrant only that this product is free of defects, since many factors which affect the results obtained from this product - such as weather, workmanship, equipment utilized and prior condition of the substrate - are all beyond our control. We will replace at no charge any product proved to have a material defect within 7-years of purchase, provided it has been applied in accordance with our written directions for uses we recommend as suitable for this product. Proof of purchase must be provided.

**DISCLAIMER OF WARRANTIES AND LIMITATION OF LIABILITY: THIS LIMITED WARRANTY IS IN LIEU OF ANY OTHER WARRANTIES EXPRESS OR IMPLIED INCLUDING BUT NOT LIMITED TO ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. MANUFACTURER SHALL HAVE NO LIABILITY OF ANY KIND BEYOND PRODUCT REPLACEMENT, INCLUDING FOR CONSEQUENTIAL, EXEMPLARY OR INCIDENTAL DAMAGES RESULTING FROM ANY DEFECTS OR ANY DELAYS CAUSED BY REPLACEMENT OR OTHERWISE. IF PURCHASER DOES NOT ACCEPT THESE TERMS OF HENRY'S LIMITED WARRANTY, PURCHASER MAY RETURN WITHIN 30-DAYS OF PURCHASE ALL CONTAINERS OR PACKAGES OF PRODUCT PURCHASED FOR A FULL REFUND (PROVIDED THE CONTAINERS OR PACKAGING IS UNOPENED AND LESS SHIPPING CHARGES IF ANY). RETENTION OF PRODUCT BEYOND 30-DAYS FROM PURCHASE, OR USE OF PRODUCT SHALL CONSTITUTE ACCEPTANCE OF HENRY'S LIMITED WARRANTY TERMS, CONDITIONS AND DISCLAIMERS. THIS LIMITED WARRANTY PROVIDES THE PURCHASER'S EXCLUSIVE REMEDY FOR ANY DEFECT IN THE PRODUCT.** To the extent that any part of this LIMITED PRODUCT WARRANTY AND LIABILITY DISCLAIMER is determined unenforceable under the law of the place of purchase of the product, that part is severed and the remainder of these terms remain in full force and effect. To the extent permitted by law, the duration of any implied warranties is limited to the duration of Henry's express warranty.

Cool Roof Rating Council ratings are determined for a fixed set of conditions, and may not be appropriate for determining seasonal energy performance. The actual effect of solar reflectance and thermal emittance on building performance may vary. Manufacturer of product stipulates that these ratings were determined in accordance with the applicable Cool Roof Rating Council procedures.

For more information, visit [www.henry.com](http://www.henry.com) or for technical assistance call us at 800-486-1278. Refer to the Safety Data Sheet prior to using this product. The Safety Data Sheet is available at [www.henry.com](http://www.henry.com) or by emailing Henry® Product Support at [productsupport@henry.com](mailto:productsupport@henry.com) or by calling 800-486-1278.

® Henry, 107, 204, 208 and 208R are registered trademarks of Henry Company

The technical and application information herein is based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use. Henry® Company data sheets are updated on a regular basis; it is the user's responsibility to obtain and to confirm the most recent version. Information contained in this data sheet may change without notice.