Olympic Maximum Semi-Transparent Stain + Sealer

GENERAL DESCRIPTION

Stain your deck or exterior wood when you want, not when the weather dictates. This semi-transparent wood stain adds subtle color, while allowing wood grain and texture to show. *Olympic Maximum* exterior wood stain allows you to clean and stain your deck in the same day, even after rain. The enhanced waterproofing wood protection can be applied in hot and cool temperatures, so you can prep your wood surface in almost any season. Bring Maximum beauty and protection to your wood surfaces.

RECOMMENDED SUBSTRATES

Decks	Railings
Fences	Siding
Outdoor Furniture	Wood

FEATURES / BENEFITS

Stain + Sealant in One—Protect and Beautify in One Step
Penetrating Formula for Strong Protection
Advanced SUNBLOCK® U.V. Protection
Exclusive SCUFF GUARD® Formula
Provides a Mildew Resistant Coating
Enhanced Waterproofing Protection
Easy Water Cleanup
Weather-Ready Application—Clean and Stain on the Same Day Even After Rain, Mist and Apply on Hot Sunny Days, Ready for Rain in 2 Hours, and Apply Down to 35°F

CONFORMANCE STANDARDS

MPI Approved in Categories #33 and #156

PRODUCT INFORMATION

79550A	Neutral Base (Must Be Tinted)*
79551A	ST-2005 Cedar Naturaltone
79552A	717 Redwood Naturaltone
79553A	Clove Brown

*Refer to the appropriate color formula book, automatic tinting equipment, and or computer color matching system for color formulas and tinting instructions.

PACKAGING

1-Gallon (3.78 L)
5-Gallon (18.9 L)

Not all products available in all sizes.

PRODUCT DATA

PRODUCT TYPE:	Acrylic/Oil
VOLUME SOLIDS*:	17% +/- 2%
WEIGHT SOLIDS*:	19% +/- 2%
WEIGHT/GALLON*:	8.5 lbs. (3.9 kg) +/- 0.2 lbs. (91 g)
VOC:	< 100 g/L (0.8 lbs./gal.)

*Product data calculated on 79550A.

COVERAGE: Approximately 250 to 350 sq. ft. (23 to 33 sq. meters) per gallon (3.78 Liters) depending on application technique, wood texture and porosity. Coverage figures do not include loss due to surface irregularities and porosity or material loss due to application method or mixing.

DRYING TIME: Normally dries in 24 hours when applied in optimal temperatures of 50°F (10°C) to 90°F (32°C). Application in high humidity or in temperatures below 50°F (10°C) may prolong drying times. Allow 24 to 48 hours of drying time before light foot traffic or replacing furniture.

READY FOR RAIN: Allow paint film to dry for at least 2 hours prior to expected rain when temperatures are at or above 60°F (16°C) and 50 to 70% relative humidity. Lower temperatures, higher humidity, or deeper colors may increase drying time and rain readiness time.

CLEANUP: Clean brushes and tools with warm, soapy water.

DISPOSAL: Contact your local environmental regulatory agency for guidance on disposal of unused product. Do not pour down a drain or storm sewer.

FLASH POINT: Over 200ºF (93ºC)

LIMITATIONS OF USE

FOR EXTERIOR USE ONLY. FOR WOOD SUBSTRATES ONLY.

Apply when air and surface temperatures are between 35°F (2°C) and 120°F (49°C) and at least 5°F (3°C) above the dew point. Air and surface temperatures must remain between 35°F (2°C) and 120°F (49°C) for the next 24 hours. If the surface is too hot to touch, lightly mist the surface using a garden hose to cool the surface before application of the stain. Caution: Avoid direct skin contact with hot surfaces. Avoid staining in direct sunlight

While this product provides a mildew resistant coating, growth may still occur if the substrate is not properly prepared prior to painting and/or if the substrate is consistently exposed to conditions conducive to mold, mildew, and algae. Examples of these conditions include, but are not limited to, under eaves, behind shrubbery and trees, and in areas that are consistently damp with little to no direct sunlight.

PROTECT FROM FREEZING.

Olympic Maximum Semi-Transparent Stain + Sealer

GENERAL SURFACE PREPARATION

Surface must be clean. Remove all dust, dirt, mildew, oil, loose wood fibers, and other contaminants. Previous coatings must be completely removed. To ensure proper penetration, weathered, dirty, or mildewed surfaces should be cleaned with a wood cleaner prior to applying stain. After rinsing, ensure surface is free of standing water. Sand all cleaned wood using 80-120 grit sandpaper for vertical surfaces and 60-80 grit sandpaper for horizontal surfaces. Always sand in direction of the wood grain and remove sanding dust. Test wood for absorbency by sprinkling water on the surface—if water is absorbed within 30 sec. to 2 min., depending on climate, the surface is ready for staining.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust or fumes. LEAD IS TOXIC. EXPOSURE TO LEAD DUST OR FUMES CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a properly fitted NIOSH-approved respirator and prevent skin contact to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the USEPA National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead. In Canada, contact a regional Health Canada office. Follow these instructions to control exposure to other hazardous substances that may be released during surface preparation.

NEW WOOD and PRESSURE TREATED LUMBER: Mill glaze must be removed and wood must pass water absorption test.

APPLICATION INFORMATION

Stir thoroughly and often during use. When using more than one container of the same color, intermix to ensure color uniformity. Apply to a small area and allow stain to dry to ensure acceptable appearance and penetration. USE WITH ADEQUATE VENTILATION. KEEP OUT OF REACH OF CHILDREN. Read all label and Safety Data Sheet (SDS) information prior to use. SDS are available through our website or by calling 1-800-441-9695.

Application Method: Apply one thin coat. To help avoid lap marks, apply to only a few boards at a time, and maintain a wet edge. Do not saturate or puddle on horizontal surfaces.

Application Equipment: Apply with a high-quality brush, paint/stain-pad, or with spray equipment. When applying by roller or spray, always backbrush for best results.

Spray equipment must be handled with due care and in accordance with manufacturer's recommendations. High pressure injection of coatings into the skin by airless equipment may cause serious injury.

Thinning: Do not thin.

Permissible temperatures during application:
Material: 35 to 90ºF (2 to 32ºC) Ambient: 35 to 120ºF (2 to 49ºC) Substrate: 35 to 120º (2 to 49ºC)

PRECAUTIONS

For warning information, please refer to the product label and SDS available at the online listing for this product at www.pittsburghpaintsco.com. Keep container tightly closed and sealed until ready for use. SDS, spill, and emergency information are available by calling 1-833-477-1553.

© 2026 The Pittsburgh Paints Co. All Rights Reserved. *Olympic, Olympic and Design, Paintbrush Design, Maximum,* and *Weather-Ready* are registered trademarks, and the *P Logo & Pittsburgh Paints* are trademarks of The Pittsburgh Paints Co.

The Pittsburgh Paints Co. believes the technical data presented is currently accurate: however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, call 1-800-441-9695.

PITTSBURGH PAINTS CO.

The Pittsburgh Paints Company
500 Cranberry Woods Drive
Cranberry Township, PA 16066
www.olympic.com

Technical Services
1-800-441-9695