


SharkBite™ PEX-a **Red PEX-a Tubing**

SharkBite™ PEX-a is a cross-linked polyethylene tubing designed for use in residential and commercial applications.

Specification Data



Tubing	Tubing Dimensions				
Nominal Size (CTS)	O. D. (in)	Wall Thickness (in)	Approx. I.D. (in)	Weight per ft. (lb.)	Volume per ft. (gal.)
1/2"	0.625 ± 0.004	0.070 + 0.010	0.475	0.053	0.009
3/4"	0.875 ± 0.004	0.097 + 0.010	0.671	0.102	0.018

Tolerances referenced from ASTM F876.

Applications

Potable water distribution, radiant heating, direct burial, embedded in concrete, snow & ice melting, geothermal groundloops, turf conditioning, municipal water service lines, fire suppression & plenum application.

Materials

Cross-Linked Polythethylene / PEX-a / Peroxide Method

Materials Designation Code - PEX 5206				
(5) Chlorine Resistance	Rated to continuously recirculate hot water at 140°F (40°C)			
(2) UV Resistance	Three-month UV resistance			
	160 psi @ (33°F - 70°F) (0.5°C - 21°C)			
(06) Hydrostatic Stress	100 psi @ 180°F (80°C)			
	80 psi @ 200°F (93°C)			

Certifications & Listings

ASTM F876, ASTM F877, NSF/ ANSI 14, NSF/ANSI/CAN 61, NSF/ ANSI/CAN 372, ASTM F2023, ASTM F2657, CSA B137.5, ASTM E84CAN/ULC S102.2, ASTM E119CAN/ULC S101



NSI:	c UHI ®
Refer to lo	cal plumbing code

Part number and description			
Part #	PEX Tubing (Coil)		
UA60R100	1/2" 100' Coil		
UA70R100	3/4" 100' Coil		

PEX Tubing (Straight Length)
1/2" 10 ' Straight Length
3/4" 10 ' Straight Length

Bend Radius

Unsupported Bend Radius = 6 X O.D.

Expansion & Contraction Rate

Expansion rate: 1.1" / 10°F / 100'

For more technical data, visit the product at: https://www.sharkbite.com/products/potable-pex-a

Product Submittal		
Name		
Date		
Architect/Owner		
Contractor		
Tag		
Notes		

Rev 1.1 / 01-21-22 **EN-US**

