



**AMERICAN ACCENTS
 STONE SPRAYS**

DESCRIPTION AND USES

Rust-Oleum® American Accents® Stone Sprays provide a unique textured finish designed for use on wood, metal, ceramic, and more.

PRODUCTS

SKU (12 ounces)	Description
238322	Tuscan Rock
223324	Mineral Brown
238325	Canyon Moss
7990830	Bleached Stone
7991830	Black Granite
7992830	Gray Stone
7994830	Sienna Stone
7995830	Pebble

PRODUCT APPLICATION

PAINTING CONDITIONS

Use outdoors or in a well ventilated area such as an open garage. Use when temperature is between 50-90°F (10-32°C) and humidity is below 65% to ensure proper drying. Do not apply to surfaces, when heated, exceed 200°F (93°C). Avoid spraying in very windy and dusty conditions. Cover surrounding area to protect from spray mist.

SURFACE PREPARATION

Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with a commercial detergent, or other suitable cleaning method. Rinse with fresh water and allow to thoroughly dry. Remove loose paint and rust with a wire brush or sandpaper. Lightly sand glossy surfaces to create a surface profile.

WARNING! If you scrape, sand or remove old paint from any surface, you may release lead paint dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE; ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

PRODUCT APPLICATION

PRIMING

Use of Rust-Oleum American Accents 7980 Aerosol Primer promotes adhesion and enhances hiding and is especially recommended for bare wood and metal. For best results, apply a base coat of a color that blends well with the stone finish.

APPLICATION

Shake can vigorously for one minute after the mixing ball begins to rattle. If mixing ball fails to rattle DO NOT STRIKE CAN. Contact Rust-Oleum. Shake often during use. Hold can upright 10-16" from surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Keep the can the same distance from the surface. Keep the can in motion while spraying. Apply two or more light coats a few minutes apart to avoid drips and runs. **Do not use near open flame.**

DRY & RECOAT

Dry and recoat times are based on 70°F and 50% relative humidity. Allow more time at cooler temperatures. Dries to touch in 15 minutes, dries to handle in 30 minutes and is fully dry in 24 hours. Recoat at anytime.

CLEAN-UP

When finished spraying, clear spray by turning can upside down and depressing spray button for 3-5 seconds (some paint will be sprayed out, so be careful to not inadvertently spray yourself or other objects). Clean-up wet paint with xylene or mineral spirits. Properly discard empty container. Do not burn or place in home trash compactor.

CLOGGING

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not insert any object into can valve opening.

TECHNICAL DATA

AMERICAN ACCENTS STONE SPRAYS

PHYSICAL PROPERTIES

		STONE SPRAYS
Resin Type		Water-based Acrylic
Pigment Type		Varies with color
MIR		1.2 Max
Fill Weight		12 ounces
Solvents		Acetone, Water
Recommended Dry Film Thickness (DFT) per Coat		1.0-2.0 mils (25-50μ)
Practical Coverage at Recommended DFT (assumes 15% material loss)		10-12 sq.ft./can (0.9-1.09 m ² /can)
Dry Times at 70°F (21°C) and 50% Relative Humidity	Touch	15 minutes
	Handle	30 minutes
	Recoat	At anytime
Shelf Life		5 years
Flash Point		-156°F (-104°C)
Safety Information		For additional information, see MSDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.