



**RUST-OLEUM® HOME ADVANCED
PAINT + PRIMER INTERIOR WALL PAINT**

DESCRIPTION AND USES

Paint confidently with Rust-Oleum® HOME Advanced Paint + Primer Interior Wall Paint. A ready-to-use formula in designer colors provides great results, first time, every time. Our advanced paint and primer offers excellent hide & coverage, with superior washability and a mold and mildew resistant coating.

PRODUCTS

| DESCRIPTION (Gallon) | SKU |
|-------------------------|--------|
| Flat White | 365473 |
| Flat French Linen | 365476 |
| Flat Sandbank | 365477 |
| Flat Uptown Café | 365479 |
| Flat Papyrus | 365480 |
| Flat Over The Moon | 365481 |
| Flat Main Street | 365482 |
| Flat Summer Storm | 365484 |
| Flat Black | 366942 |
| Eggshell White | 365485 |
| Eggshell French Linen | 365488 |
| Eggshell Sandbank | 365489 |
| Eggshell Uptown Café | 365491 |
| Eggshell Papyrus | 365492 |
| Eggshell Over The Moon | 365493 |
| Eggshell Main Street | 365494 |
| Eggshell Summer Storm | 365496 |
| Eggshell Sweetheart | 365498 |
| Eggshell Ripple | 365500 |
| Eggshell North Shore | 365501 |
| Eggshell Black | 365502 |
| Semi-Gloss White | 365503 |
| Semi-Gloss French Linen | 365506 |
| Semi-Gloss Sandbank | 365507 |
| Semi-Gloss Black | 365509 |

PRODUCT APPLICATION

**READ ALL DIRECTIONS BEFORE BEGINNING PROJECT
SURFACE PREPARATION**

Surface must be free of any dust, grease, oil, stains, rust or any other contaminants. Sand glossy surfaces before painting and wash walls if necessary. Fill in any cracks or holes to ensure a smooth surface. Drywall joint compound must dry for two days. New drywall and bare wood should be primed before painting. Allow new plaster to cure for 30 days before painting.

PRODUCT APPLICATION (cont.)

SURFACE PREPARATION (cont.)

We recommended the use of Zinsser Bulls Eye 1-2-3® Primer to protect new drywall, painting over contrasting colors, bare woods and metals or where paint adhesion could propose a problem.

WARNING: If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

COVERAGE/WHERE TO USE

One gallon will cover up to 400 sq. ft. depending on surface texture, porosity, and application method. Dark colors may require multiple coats. Ideal for interior walls, trim, windows, and doors. Surfaces - Drywall, masonry and wood.

NOTE: Do not use on floors.

APPLICATION

Stir well before use. Intermix cans of the same color and product to ensure color consistency. Apply using a high quality 3/8"-1/2" nap roller or a high quality brush. If using an airless sprayer, follow manufacturer's instructions for use, and use a .013"-.017" tip at 1800-2300 psi, adjusting as needed. Apply using even strokes, moving from dry to wet areas, keeping a wet edge. Two coats are required for new or uncoated surfaces. Some colors may require additional coats. Thinning is not recommended.

DRY AND RECOAT TIMES

Based on 77°F (25°C) <50% humidity, dries to the touch in one hour. May be recoated after four hours. Allow more time to dry at cooler temperatures or in high humidity.

CLEAN-UP


Clean hands, tools, spills and splatters with soap and warm water.

DISPOSAL

To dispose of empty containers and unused product, contact your local environmental regulatory agency.

MAINTENANCE CARE

Do not place objects on painted surfaces until thoroughly dry. Freshly painted surfaces may be washed after 30 days. Clean with mild, non-oily soap and water.

| | | |
|---|--|----------------|
| | TECHNICAL DATA | ROC-189 |
| • TRUSTED QUALITY SINCE 1921 •  | RUST-OLEUM® HOME ADVANCED PAINT + PRIMER INTERIOR WALL PAINT | |

PHYSICAL PROPERTIES

| | | HOME ADVANCED PAINT + PRIMER INTERIOR WALL PAINT |
|--|-------------------|--|
| Resin Type | | Styrene Acrylic |
| Pigment Type | | Varies by color |
| Solvents | | Water, Glycol Ethers |
| Weight | Per Gallon | 10.0-11.7 lbs. |
| | Per Liter | 1.15-1.4 kg |
| Solids | By Weight | 51.5-59.5% |
| | By Volume | 40-44% |
| Volatile Organic Compounds | | <50 g/L |
| Recommended Dry Film Thickness (DFT) per Coat | | 1.5-2.0 mils (37.5-50µ) |
| Wet Film to Achieve DFT (unthinned material) | | 2.5-5 mils (62.5-125µ) |
| Practical Coverage at Recommended DFT (assumes 15% material loss) | | Gallon up to 400 sq.ft. Depending on application method and surface porosity |
| Dry Times at 77°F (25°C) and 50% Relative Humidity | Touch | 1 hour |
| | Recoat | 4 hours |
| | Full Cure | 7-10 days |
| Shelf Life | | 3 years |
| Flash Point | | >200°F (93°C) |
| Storage | | PROTECT FROM FREEZING |
| Safety Information | | For additional information, see SDS |

Calculated values are shown and may vary from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



Rust-Oleum Corporation
 11 Hawthorn Parkway
 Vernon Hills, Illinois 60061

Phone: 877-815-2466
www.rustoleum.com

Form: ARJ-2105
 Rev.: 071520