

### PPG Ceiling Paint Interior Paint + Primer

#### **GENERAL DESCRIPTION**

*PPG* Ceiling Paint is an interior paint primer in one that is formulated to make your ceiling paint projects easier and faster - in one coat\*. The low spatter formula leads to a low mess application and minimal cleanup. It is low odor, low VOC all backed by a Lifetime Guarantee.

Ideal for use on properly prepared, interior ceilings where a durable, premium-quality, flat finish is desired.

\*One coat coverage only when tinted to colors specified for PPG Timeless Interior Paint + Primer.

#### RECOMMENDED SUBSTRATES

Concrete Concrete/Masonry Block Plaster

## FEATURES / BENEFITS

- Complete one coat coverage\*
- · True Flat Finish Hides Minor Imperfections
- Stain Blocking
- · Low Spatter, Low Mess Application
- Low Odor, Low VOC

\*One coat coverage only when tinted to colors specified for PPG Timeless Interior Paint + Primer.

## PRODUCT INFORMATION

PPG83-610 Ceiling White

#### **PACKAGING**

1-Gallon (3.78 L) 5-Gallon (18.9 L)

Not all products are available in all sizes.

#### PRODUCT DATA

 PRODUCT TYPE:
 100% Acrylic

 SHEEN:
 Flat, 0-3 @ 60°

 VOLUME SOLIDS:
 32% +/- 2%

 WEIGHT SOLIDS:
 52% +/- 2%

**VOC:** <50 g/L (0.4 lbs./gal.)

**WEIGHT/GALLON:** 11.8 lbs. (5.3 kg) +/- 0.2 lbs. (91 g)

**COVERAGE:** Approximately 300 to 400 sq. ft. (28 to 37 sq. meters) per U.S. gallon (3.78 L) on primed, smooth, nonporous surfaces.

Coverage figures do not include material loss due to surface irregularities and porosity, or material loss due to application method or mixing.

Some colors, drastic color changes, or porous surfaces may require more than one coat to achieve a uniform finish.

Wet Film Thickness: 4.0 mils to 5.3 mils

Wet Microns: 102 to 134

Dry Film Thickness: 1.2 mils to 1.6 mils

Dry Microns: 30 to 40

Coverage figures do not include loss due to surface irregularities and porosity or material loss due to application method or mixing.

**DRYING TIME:** Dry time @ 77°F (25°C); 50% relative humidity.

To Touch: 1 hour To Recoat: 4 hours

Drying times listed may vary depending on temperature, humidity, film build, color, and air movement.

Wait at least 30 days after painting before cleaning the surface with a non-abrasive, mild cleanser. Very deep colors may require longer to fully cure.

CLEANUP: Clean brushes and tools with warm, soapy water.

**DISPOSAL:** Contact your local environmental regulatory agency for guidance on disposal of unused product. Do not pour down a drain or storm sewer.

FLASH POINT: Over 200°F (93°C)

## LIMITATIONS OF USE

FOR INTERIOR USE ONLY. Apply when air, product and surface temperatures are between 50°F (10°C) and 90°F (32°C). USE WITH ADEQUATE VENTILATION. KEEP OUT OF REACH OF CHILDREN. Read all label and Safety Data Sheet (SDS) information prior to use. SDS are available through our website or by calling 1-800-441-9695.

Not recommended for use on floors or in high humidity areas.

PROTECT FROM FREEZING.

PPG PPG83-610

## PPG Ceiling Paint Interior Paint + Primer

## GENERAL SURFACE PREPARATION

Surface must be clean and dry. Remove all loose, peeling paint, dirt, grease, and any other surface contaminants. Putty all nail holes and caulk all cracks and open seams. Sand all glossy, rough, and patched surfaces. Plaster, concrete, and masonry surfaces must be completely dry, free of efflorescence, and allowed to cure for 30 days prior to painting. When applied to an uncoated substrate or to bare wood, two coats are required with the first coat acting as the primer. Uncoated substrates, repaired surfaces, or lightly stained areas may require additional coats. For severe stains, water marks, and other challenging conditions, such as bare metal or chalky surfaces, use an appropriate specialty primer.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust or fumes. LEAD IS TOXIC. EXPOSURE TO LEAD DUST OR FUMES CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a properly fitted NIOSH-approved respirator and prevent skin contact to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the USEPA National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead. Follow these instructions to control exposure to other hazardous substances that may be released during surface preparation.

**CONCRETE:** New concrete should cure for at least 30 days and preferably 90 days prior to painting. The pH of the substrate must be less than 10 before painting.

**CONCRETE/MASONRY BLOCK:** Mortar should cure for at least 30 days and preferably 90 days prior to painting. Fill block with an appropriate block filler. Surfaces previously coated with water thinned cement-based paint must be prepared with extra care. If the material appears to be adhering tightly, a masonry sealer may be applied to seal the surface. Check adhesion by applying a piece of masking tape. If the sealer peels off and has loose particles, remove all chalking or crumbling material, re-seal and re-check adhesion.

FERROUS METAL: The surface must be cleaned thoroughly to remove any dust, rust, and surface contaminants, and then primed.

PLASTER: Plaster, hardcoat, skim coat, or other alkaline surfaces should be allowed to cure for at least 30 days prior to painting.

**WOOD:** Unpainted wood or wood in poor condition should be sanded smooth, wiped clean. Any knots or resinous areas must be primed before painting. Countersink all nails, putty flush with surface.

# APPLICATION INFORMATION

Stir thoroughly. Apply with a high-quality brush, roller, paint pad, or by spray equipment. When using more than one container of the same color, intermix to ensure color uniformity. Do not thin. Apply only when air, product, and surface temperatures are between 50°F (10°C) and 90°F (32°C).

**Airless Spray**: For airless spray application, use tip size .015" - .021" and pressure range of 1500 – 2000 psi. Spray equipment must be handled with due care and in accordance with manufacturer's recommendation. High-pressure injection of coatings into the skin by airless equipment may cause serious injury.

**Brush:** Polyester/Nylon Brush

Roller: 3/8" nap roller cover for smooth surfaces and up to 3/4" for rough or textured surfaces

Thinning: DO NOT THIN

Permissible temperatures during application:

Material: 50 to 90°F 10 to 32°C Ambient: 50 to 90°F 10 to 32°C Substrate: 50 to 90°F 10 to 32°C

## **PRECAUTIONS**

**WARNING! HARMFUL IF INHALED.** Sanding and grinding dusts may be harmful if inhaled. This product contains crystalline silica which can cause lung cancer or silicosis. The risk of cancer depends on the duration and level of exposure to dust from sanding surfaces or mist from spray applications. Do not breathe vapor or mist. Do not swallow. Do not get on skin or clothing. Keep container tightly closed and sealed until ready for use. Wash thoroughly after handling. Provide fresh air ventilation during and after application and drying. Avoid the inhalation of dust, particulates, spray or mist arising from the application of this preparation. Use personal protective equipment as required. **FIRST AID:** If swallowed, rinse mouth with water (only if the person is conscious). Do not induce vomiting unless directed to do so by medical personnel. If in eyes, rinse with water for 15 minutes. Check for and remove any contact lenses. If on skin, rinse well with water. Wash with soap and water. Get medical attention if irritation develops. If inhaled, remove to fresh air. Call physician immediately. Keep out of the reach of children. For workplace use, an SDS is available from your retailer or by calling (412) 492-5555. EMERGENCY SPILL INFORMATION: (412) 434-4515 (U.S.)

© 2020 PPG Industries, Inc. All Rights Reserved. The PPG Logo is a registered trademark of PPG Industries Ohio, Inc.

PPG Architectural Finishes, Inc. believes the technical data presented is currently accurate: however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, call 1-800-441-9695.

