

How to Apply Elastomeric Roof Coatings



STEP 1: PREPARE THE SURFACE

- **Clear roof surface** of loose debris including dirt, gravel, sticks, etc. using a push broom or blower
- **Clean** with a pressure washer.
- **Patch and repair** cracks, blisters and other problem areas using **White Roof Patch**, following label directions. Reinforce repairs with **Universal Patching Fabric**.

RECOMMENDED SURFACES

- Metal
- Urethane/polystyrene foam
- Concrete roofs
- Aged rolled roofing and aluminum coatings
- Flat and barrel cement tile



STEP 2: APPLY ELASTOMERIC COATING

On a clear, warm, sunny day, roll, brush or spray Elastomeric Roof Coating to a dry roof surface. Follow all label directions.

RECOMMENDED APPLICATORS

Roof brush, ¾" nap roller, or airless spray in 10"-12" pattern, 2000 psi, .021 to .025 spray tip

COVERAGE RATES: TWO COATS RECOMMENDED

Metal	80 to 100 sq. ft. per a gallon
Foam	50 to 75 sq. ft. per a gallon
Concrete tile	50 to 75 sq. ft. per a gallon