



PHYSICAL PROPERTIES (FLOATING MULTILAYER MODULAR FLOORING) - 8.0MM GAUGE

Collection	Plank - XL	Plank - XXL
Size	8.7"x59.4" (220mm x 1510mm)	8.7"x72" (220mm x 1828.8mm)
Overall Gauge	8.0mm (0.315")	8.0mm (0.315")
Wear Layer	12mil (0.3mm)	21.7mil (0.55mm)
Top Layer	2.0mm (0.079") LVT	2.0mm (0.079") LVT
Core	5.0mm (0.197") Rigid Core	5.0mm (0.197") Rigid Core
Pad	1.0mm (0.039") HDPE	1.0mm (0.039") HDPE
Use	Light Commercial & Residential	Light Commercial & Residential
Profile	Micro-Bevel	Bevel
Finish	Enhanced Ceramic Bead	Enhanced Ceramic Bead
Ultra-Fresh	Included in Finish and Pad	Included in Finish and Pad
Embossing(s)	In-Register	In-Register, Natural Timber
Pieces/Carton	6 pieces	6 pieces
Coverage/Carton	21.45 Sq.Ft. (1.99 Sq.M.)	25.98 Sq.Ft. (2.41 Sq.M.)
Limited Warranty	Light Commercial - 10 Years Residential - Lifetime	Light Commercial - 10 Years Residential - Lifetime

STANDARDS – SAFETY & PERFORMANCE

Standard	Description	Requirements	Results
ASTM E648	Critical Radiant Flux (Radiant Panel)	Class I: $\geq 0.45 \text{ W/cm}^2$	Passes Requirements ¹
ASTM E662	Smoke Density	Flaming & Non-Flaming ≤ 450	Passes Requirements ²
ASTM D2047	Coefficient of Friction (Slip Resistance)	Not Applicable (No Official Requirements)	≥ 0.6 (Dry)
ASTM F970	Static Load	Plank - XL: No Requirements Plank - XXL: $\pm 0.005"$, 250psi	Plank - XL: Not Applicable Plank - XXL: Passes Requirements
SIM Test	Static Load Limit	Test to Limit ($\pm 0.005"$)	≥ 500 psi
ASTM F2199	Dimensional Stability	Plank - XL: $\leq 0.25\%$ / lineal ft. Plank - XXL: $\leq 0.2\%$ / lineal ft.	Plank - XL: Surpasses Requirements Plank - XXL: Surpasses Requirements
ASTM F925	Chemical Resistance	No more than "Slight Change"	Surpasses Requirements
ASTM F1514	Resistance to Heat	Average $\Delta E < 8.0$	Surpasses Requirements
ASTM F1515	Resistance to Light	Average $\Delta E < 8.0$	Surpasses Requirements
ASTM G21	Antifungal Activity	Not Applicable (No Official Requirements)	Top: 0-1; Bottom: 0-1 ³
ASTM F963	Heavy Metals	Refer to Standard	Passes Requirements
ASTM D7823	Phthalates	Refer to CPSIA ⁴	Passes Requirements
ASTM F410	Wear Layer Thickness	Plank - XL: No Requirements Plank - XXL: $\geq 0.020"$ (0.5mm)	Plank - XL: Not Applicable Plank - XXL: Passes Requirements

STANDARDS – SOUND

Assembly	ASTM E90	ASTM E492	ASTM E2179	Results (Remarks)
6" Concrete Slab	STC 50	IIC 50	Δ IIC 24	All tested assemblies pass IBC ⁵ requirements of STC ≥ 50 and IIC ≥ 50 for multi-story dwellings
8" Concrete Slab	STC 53	IIC 55	Not Applicable	
6" Concrete Slab with Drop-Ceiling	STC 62	IIC 70	Not Applicable	

Notes

- 1) ASTM E648 - Critical Radiant Flux (Radiant Panel): Passes Requirements for Class I per International Building Code (IBC) 2018 & NFPA 101 Life Safety Code
- 2) ASTM E662 - Smoke Density: 450 is the limit established by many state, county, and/or local building and/or fire codes, but is not set as a limit for (resilient) flooring products nationwide. Thus, Smoke Density requirements for flooring products may vary from jurisdiction to jurisdiction.
- 3) ASTM G21 - Antifungal Activity: Top Surface (LVT Top Layer) and Bottom Surface (Pad) scored 0-1 (No Growth to <10% Growth)
- 4) CPSIA = Consumer Product Safety Improvement Act
- 5) IBC = International Building Code

Ultra-Fresh is a registered trademark of Thomson Research Associates, Inc.